


FREIOTHERM-Hydro-Coating


WO1892M

Characteristics	<ul style="list-style-type: none"> ■ Water-thinnable baking coating ■ Application, e.g. in the mechanical engineering and plant construction sector ■ Good scratch resistance ■ Good hot water resistance ■ Good adhesion to steel and non-ferrous metals ■ Good hardness and elasticity 																						
Technical / Physical Data	<table border="1"> <tr> <td>■ Binder-Base</td> <td>Combination of polyester/amino resin</td> </tr> <tr> <td>■ Colour</td> <td>All common colour shades</td> </tr> <tr> <td>■ Gloss value <small>visual</small></td> <td>mat</td> </tr> <tr> <td>■ Viscosity <small>DIN 53211 (formerly)</small></td> <td>Flow time 50-60 seconds 4 mm viscosity cup</td> </tr> <tr> <td>■ Thinner</td> <td>demineralised water</td> </tr> <tr> <td>■ pH-Value</td> <td>8,3-8,7</td> </tr> <tr> <td>■ Density <small>calculated</small></td> <td>1,2-1,4 g/ml</td> </tr> <tr> <td>■ Solid Mass <small>calculated</small></td> <td>48-60 %</td> </tr> <tr> <td>■ Solid content in volume <small>calculated</small></td> <td>280-320 ml/kg</td> </tr> <tr> <td>■ Material usage <small>theoretical, without application loss</small></td> <td>250-270 g/m², Layer thickness 80 µm</td> </tr> <tr> <td>■ Reference colour of the specified values</td> <td>Colour of WO1892MRA916</td> </tr> </table>	■ Binder-Base	Combination of polyester/amino resin	■ Colour	All common colour shades	■ Gloss value <small>visual</small>	mat	■ Viscosity <small>DIN 53211 (formerly)</small>	Flow time 50-60 seconds 4 mm viscosity cup	■ Thinner	demineralised water	■ pH-Value	8,3-8,7	■ Density <small>calculated</small>	1,2-1,4 g/ml	■ Solid Mass <small>calculated</small>	48-60 %	■ Solid content in volume <small>calculated</small>	280-320 ml/kg	■ Material usage <small>theoretical, without application loss</small>	250-270 g/m ² , Layer thickness 80 µm	■ Reference colour of the specified values	Colour of WO1892MRA916
■ Binder-Base	Combination of polyester/amino resin																						
■ Colour	All common colour shades																						
■ Gloss value <small>visual</small>	mat																						
■ Viscosity <small>DIN 53211 (formerly)</small>	Flow time 50-60 seconds 4 mm viscosity cup																						
■ Thinner	demineralised water																						
■ pH-Value	8,3-8,7																						
■ Density <small>calculated</small>	1,2-1,4 g/ml																						
■ Solid Mass <small>calculated</small>	48-60 %																						
■ Solid content in volume <small>calculated</small>	280-320 ml/kg																						
■ Material usage <small>theoretical, without application loss</small>	250-270 g/m ² , Layer thickness 80 µm																						
■ Reference colour of the specified values	Colour of WO1892MRA916																						
Substrate	<ul style="list-style-type: none"> ■ Aluminium ■ Aluminium, pretreated ■ Steel ■ Steel - preliminary test required for galvanised substrates ■ Steel, passivated or pretreated substrates 																						
Pretreatment	<ul style="list-style-type: none"> ■ The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. For more stringent requirements, we recommend: for corrosion protection - e.g. phosphating for adhesion - e.g. blasting, pickling, sanding 																						
Structure recommendation	<table border="1"> <tr> <td>■ Substrate</td> <td>Aluminium</td> </tr> <tr> <td>■ Base coat</td> <td>WO1892MRA916 Dry film thickness 30 µm</td> </tr> </table>	■ Substrate	Aluminium	■ Base coat	WO1892MRA916 Dry film thickness 30 µm																		
■ Substrate	Aluminium																						
■ Base coat	WO1892MRA916 Dry film thickness 30 µm																						
Mechanical Test	<table border="1"> <tr> <td>■ Cross-cut-test <small>DIN EN ISO 2409</small></td> <td>Gt 0</td> </tr> </table>	■ Cross-cut-test <small>DIN EN ISO 2409</small>	Gt 0																				
■ Cross-cut-test <small>DIN EN ISO 2409</small>	Gt 0																						


Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating
WO1892M

	<ul style="list-style-type: none"> Chemical resistance Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.
<p>Processing and application</p>	<ul style="list-style-type: none"> Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. Dry film thickness must not exceed 40 µm - risk of reaction bubbles. Object temperature 10-30 °C Processing conditions Room temperature 18-25 °C Relative humidity 40-60 % High pressure spraying as delivered viscosity Nozzle: 1,4 mm Spray pressure 3-4 bar Electrostatic possible, system-specific Cleaning of equipment Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424. Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<p>Curing</p>	<ul style="list-style-type: none"> Oven drying 30 min./ 180 °C - 15 min./ 200 °C Object temperature green cross-hatching = baking conditions with good final properties 
<p>Resistance to storage</p>	<ul style="list-style-type: none"> Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time. <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance</p>

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating
WO1892M

	<p>purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>
Specific comments	<ul style="list-style-type: none"> ■ EFD-info Refer to the EFD information for further technical information. Nr. 111 ■ Test conditions All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. <p>The information provided here contains reference values and does not constitute a specification.</p>