



KL1753M

FREOLUX-Welding Primer

Product description

Product technology	solvent-based 1K coating
Drying	quickly
Substrate	Steel

General product properties

Binder-Base	Alkyd resin	
Colour	in accordance with RAL 840 HR other colours on request	
Gloss visually	matt	
Viscosity	Flow time 35-45 sec., 4 mm flow cup	DIN 53211
Density	1,3-1,5 g/ml	theoretical
Solid mass	63-65 %	theoretical
Solid content in volume	36-46 %	theoretical
Reference product	The specified values refer to the product KL1753MRU804.	
Resistance to storage	<p>approx. 18 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	Steel
	Primer	KL1753M Dry film thickness 10-30 µm
	Intermediate layer	KL1712M Dry film thickness 50-70 µm



KL1753M

FREOLUX-Welding Primer

	Top coat	KL1022G	
		Dry film thickness 40-60 µm	
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).		
Thinning	EFD dilution 400320 EFD dilution 400474		
Processing conditions	from 10 °C to 25 °C		
Airless spraying	as delivered viscosity		
High pressure spraying	25-30 sec. / 4 mm Flow cup Nozzle 1,4 mm Injection pressure 3-4 bar		DIN 53211
Material usage	without application loss 65-73 g/m² layer thickness 20 µm		theoretical
Oven drying	up to 80 °C possible (object temperature)		
Air drying	20 °C, 50 % relative humidity		
Dust drying	after 30 minutes (degree of dryness 1)		DIN EN ISO 9117-5
Dry to the touch	after 45 minutes (degree of dryness 4)		DIN EN ISO 9117-5
Full drying	after 15 day/s (pendulum damping)		DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500		

Comments

EFD info	Further technical information can be found in the EFD Info. No. 170.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>