



ZK1651G EFDEZELL-Clearcoat

Product description

Product technology	Solvent-based air-drying coating
Resistance to light and weather	Good light resistance
Substrate	Non-ferrous metals, Steel

General product properties

Binder-Base	Combination of nitrocellulose-/alkyd resin		
Colour	transparent		
Gloss value	high glossy	70-90 GU, angle 20°	DIN EN ISO 2813
Viscosity	Flow time 20-28 sec., 4 mm flow cup		DIN 53211
Density	0,9-1,0 g/ml	theoretical	
Solid mass	21,5-22,5 %	theoretical	
Solid content in volume	18-19 %	theoretical	
Reference product	The specified values refer to the product ZK1651GRA999.		
Resistance to storage	<p>approx. 18 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>		

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.		
Structure recommendation	Substrate	Non-ferrous metals	
	Top coat	ZK1651GRA999 Dry film thickness 20-30 µm	
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).		



ZK1651G EFDEZELL-Clearcoat

Thinning	EFD dilution 400500	
Processing conditions	from 10 °C to 25 °C	
High pressure spraying	as delivered viscosity	
Material usage	without application loss 100-105 g/m ² layer thickness 20 µm	theoretical
Oven drying	up to 100 °C possible (object temperature)	
Air drying	20 °C, 50 % relative humidity	
Dust drying	after 10 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 50 minutes (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 2 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500	

Comments

EFD info	Further technical information can be found in the EFD Info. No. 170.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.