



## PU3004B FREIOTHERM-Powder Coating

### Product description

<b>Product technology</b>	Powder coating for use on industrial exteriors		
<b>Application area</b>	e.g. in the construction and sanitary sector		
<b>Surface</b>	smooth		
<b>Gloss value</b>	glossy		
<b>Surface hardness</b>	good		
<b>Mechanical resistance</b>	good		
<b>Resistance to light and weather</b>	good		
<b>Chemical resistance</b>	very good		
<b>Temperature resistance</b>	very good		

### General product properties

<b>Binder-Base</b>	polyurethane (non-separating)		
<b>Gloss value</b>	satin glossy	70-85 GU, Angle 60°	DIN EN ISO 2813
<b>Density</b>	1,2-1,7 g/cm <sup>3</sup> depending on the shade		theoretical
<b>Resistance to storage</b>	approx. 36 month in original packagings at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place.		
The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.			

### Application and processing

<b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.		
<b>Recommended coating thickness</b>	70-90 µm		
<b>Material usage</b>	approx. 0,12 kg/m <sup>2</sup> , layer thickness 80 µm		theoretical
<b>Processing</b>	Corona		

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.

The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6  
78199 Bräunlingen-Döggingen | Deutschland  
+49 77071510  
[www.freilacke.de](http://www.freilacke.de) | [info@freilacke.de](mailto:info@freilacke.de)




## PU3004B

## FREIOTHERM-Powder Coating

### Curing

Recommended object temperature 12 min/200 °C.  
Baking window tested in colour shade RAL9005.



Objekt Temperatur in °C	200	210	215
Object Temperature in °C			

Haltezeit Minimum in Minuten	12	8	7
Holding time minimum in minutes			

Haltezeit Maximum in Minuten	45	12	10
Holding time maximum in minutes			

### Note on curing

Coloured area = stoving conditions with good end properties

The displayed baking conditions are based on results from laboratory tests and therefore merely serve as a guideline when configuring the processing company's coating systems. The processing company is responsible for ensuring that the coating is fully cured. The complete curing of the coating must be checked by means of additional analytical and resistance tests using representative original parts under production conditions. Please do not hesitate to contact us if you require consultation.

### Compatibility

Compatibility with other powder coatings must be checked.

### Further processing of coated pieces

#### Touch-up coating

on request. For details see EFD Info No. 4..



## PU3004B FREIOTHERM-Powder Coating

### Mechanical tests

<b>Sample description</b>	On steel plate 70-90 µm layer thickness 12 minutes 200°C object temperature product PU3004BRA905	
<b>Cross-cut-test</b>	Gt 0	DIN EN ISO 2409
<b>Cupping test</b>	>3 mm	DIN EN ISO 1520
<b>Impact-test</b>	>40 kg cm (front)	DIN EN ISO 6272-1

### Climatic tests

<b>Sample description</b>	On zinc-phosphated steel plate product PU3004BRA905		
<b>Condensate constant climate</b>	Load duration	1000 h	DIN EN ISO 6270-2 (CH)
	Detachment Cut	<1 mm	DIN EN ISO 4628-8
<b>Neutral salt spray test</b>	Load duration	500 h	DIN EN ISO 9227 (NSS)
	Detachment Cut	<1 mm	DIN EN ISO 4628-8

### Chemical resistance

<b>Influencing factors</b>	The chemical resistance depends on the concentration, temperature, exposure time and test method. This has to be checked depending on the application.		
----------------------------	--	--	--

### Comments

<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.