



## ER1936H\_HE0051 FREOPOX-UHS-Primer

### Product description

<b>Product technology</b>	solvent-based 2-component coating	
<b>Application area</b>	e.g. in the vehicle construction sector	
<b>Corrosion protection</b>	very good	
<b>Substrate</b>	Steel, Stainless steel, Aluminium, Galvanised steel	

### General product properties

<b>Binder-Base</b>	Epoxy resin	
<b>Colour</b>	in accordance with RAL 840 HR other colours on request	
<b>Gloss visually</b>	satin mat	
<b>Viscosity</b>	Flow time 60-85 sec., 4 mm flow cup	DIN 53211
<b>Density</b>	1,60-1,65 g/ml after addition of hardener	theoretical
<b>Solid mass</b>	71,5-75,0 % after addition of hardener	theoretical
<b>Solid content in volume</b>	49,0-54,0 % after addition of hardener	theoretical
<b>Reference product</b>	The specified values refer to the product ER1936HRU735.	
<b>Resistance to storage</b>	<p>approx. 18 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

### Application and processing

<b>Pretreatment</b>	<p>The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.</p>	
---------------------	--	--



## ER1936H\_HE0051 FREOPOX-UHS-Primer

<b>Structure recommendation</b>	Substrate	Steel blasted to Sa 2.5
	Primer	ER1936H Mixing ratio 6:1 HE0051 Dry film thickness 70-90 µm
	Top coat	UR1449G Mixing ratio 7:1 HU0140 Dry film thickness 40-60 µm
<b>Note before use</b>	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
<b>Hardener</b>	HE0051	
<b>Mixin ratio</b>	Parts by weight 6:1	
<b>Thinning</b>	EFD dilution 400424	
<b>Processing conditions</b>	from 10 °C to 25 °C	
<b>Processing time</b>	max. 3 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.	
<b>Airmix spraying</b>	as delivered viscosity after curing agent addition Nozzle 13/40 mm angle 40° Material pressure 3,0-3,5 bar Atomiser pressure 3,0 bar	
<b>High pressure spraying</b>	Set to 40-50 sec / 4 mm flow-cup after adding hardener Nozzle 1,5-2,0 mm Spray pressure 4-5 bar	DIN 53211
<b>Rolling/painting</b>	as delivered viscosity after curing agent addition	
<b>Material usage</b>	without application loss 245-265 g/m <sup>2</sup> layer thickness 80 µm after addition of hardener	theoretical
<b>Oven drying</b>	up to 70 °C possible (object temperature)	
<b>Air drying</b>	20 °C, 50 % relative humidity	
<b>Dust drying</b>	after 30 minutes (degree of dryness 1)	DIN EN ISO 9117-5
<b>Dry to the touch</b>	after 5 hours (degree of dryness 4)	DIN EN ISO 9117-5
<b>Full drying</b>	after 7 day/s (pendulum damping)	DIN EN ISO 1522
<b>Cleaning of equipment</b>	with EFD dilution 400424 within the processing time.	



## ER1936H\_HE0051 FREOPOX-UHS-Primer

### Further processing of coated pieces

---

**Repainting** after 2 hours / room temperature approx. 20 °C.

### Comments

---

**EFD info** Further technical information can be found in the EFD Info. No. 170.

**Work-and Healthprotection** The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

**Test conditions** All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.