




PX6000D FREOCRYL-Powder Coating

Curing

Recommended object temperature 10 min/180 °C.
Baking window tested in colour shade RAL9005.



Objekt Temperatur in °C Object Temperature in °C	180	200
Haltezeit Minimum in Minuten Holding time minimum in minutes	10	6
Haltezeit Maximum in Minuten Holding time maximum in minutes	45	15

Note on curing

Coloured area = stoving conditions with good end properties

The displayed baking conditions are based on results from laboratory tests and therefore merely serve as a guideline when configuring the processing company's coating systems. The processing company is responsible for ensuring that the coating is fully cured. The complete curing of the coating must be checked by means of additional analytical and resistance tests using representative original parts under production conditions. Please do not hesitate to contact us if you require consultation.

Compatibility

Compatibility with other powder coatings must be checked.

Further processing of coated pieces

Touch-up coating

on request. For details see EVS Info No. 4..

Mechanical tests

Sample description

On steel plate
60-80 µm layer thickness
10 minutes 180°C object temperature

Cross-cut-test

Gt 0

DIN EN ISO 2409

Cupping test

>3 mm

DIN EN ISO 1520

Impact-test

>60 kg cm (front)

DIN EN ISO 6272-1



PX6000D FREOCRYL-Powder Coating

Climatic tests

Sample description	On zinc-phosphated steel plate 60-80 µm layer thickness 10 minutes 180°C object temperature		
Condensate constant climate	Load duration	500 h	DIN EN ISO 6270-2 (CH)
	Detachment Cut	<1 mm	DIN EN ISO 4628-8
Neutral salt spray test	Load duration	240 h	DIN EN ISO 9227 (NSS)
	Detachment Cut	<1 mm	DIN EN ISO 4628-8

Chemical resistance

Influencing factors	The chemical resistance depends on the concentration, temperature, exposure time and test method. This has to be checked depending on the application.
----------------------------	--

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.