



## 300356

## FREIOTHERM-ATL-Levelling agent

### Product description

**Product technology** Additive for electrocoat paints

### General product properties

<b>Density</b>	0,9 - 1,1 g/cm <sup>3</sup>	theoretical
<b>Solid mass</b>	26 - 28 %	theoretical
<b>Resistance to storage</b>	approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

### Application and processing

<b>Note before use</b>	Direct addition to the basin is not possible! For a good mix, add to the overflow/weir or mixing tube! The procedure is dependant upon various factors and is therefore matched to the application technology to the individual plant.
<b>Additional quantity</b>	0,5 - 5,0 %
<b>Exposure</b>	8 hour

### Comments

<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.