



## BD7550 DURELASTIC-Accelerator

### Product description

<b>Product technology</b>	Accelerator on base of Cobaltoctoat
---------------------------	-------------------------------------

### General product properties

<b>Viscosity</b>	Flow time 12 - 15 sec., 4 mm flow cup	DIN 53211
<b>Density</b>	0,95 +/- 0,05 g/ml	theoretical
<b>Solid mass</b>	ca. 44 %	theoretical
<b>Resistance to storage</b>	<p>approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

### Application and processing

<b>Note before use</b>	Accelerator and hardener must be mixed separately to avoid curing faults and reactions.
<b>Mixin ratio</b>	Products BD7550 Parts by weight 0,2 - 2,0 %
<b>Thinning</b>	EFD dilution 400900
<b>Cleaning of equipment</b>	with EFD cleaning agent 400906 within the processing time.

### Comments

<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>