



UR1955V_HU0061 EFDEDUR-Lackfarbe

Product description

Product technology	solvent-based 2-component coating	
Application area	e.g. in the vehicle construction sector	
Application	For interior and exterior applications	
Resistance to light and weather	very good	

General product properties

Binder-Base	Acrylic Resin	
Colour	in accordance with RAL 840 HR other colours on request	
Gloss value	according to customer requirements	
Viscosity	Flow time 80-100 sec., 4 mm flow cup	DIN 53211
Density	1,05-1,20 g/ml after addition of hardener	theoretical
Solid mass	53-61 % after addition of hardener	theoretical
Solid content in volume	44-47 % after addition of hardener	theoretical
Reference product	The specified values refer to the product UR1955VRA724.	
Resistance to storage	<p>approx. 18 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	Steel
	Primer	ER1912M Mixing ratio 5:1 HE0052 Dry film thickness 70-90 µm
	Top coat	UR1955V Mixing ratio 5:1 HU0061 Dry film thickness 40-50 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	



UR1955V_HU0061 EFDEDUR-Lackfarbe

Hardener	HU0061	
Mixin ratio	Parts by weight 5:1 Volume parts 3,66:1	
Thinning	EFD dilution 400320	
Processing conditions	from 10 °C to 25 °C	
Processing time	max. 4 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.	
Airless spraying	delivery viscosity Nozzle 0,28-0,33 mm Angle 40° Material pressure 150 bar	
Airmix spraying	as delivered viscosity Nozzle 0,28-0,33 mm angle 40° Material pressure 80-100 bar Atomiser pressure 3-4 bar	
High pressure spraying	Set to 18-22 sec / 4 mm flow-cup after adding hardener Nozzle 1,8 mm Spray pressure 3-4 bar	DIN 53211
Electrostatic	possible, system-specific	
Material usage	without application loss 120-130 g/m ² layer thickness 50 µm after addition of hardener	theoretical
Air drying	20 °C, 50 % relative humidity	
Oven drying	up to 100 °C possible (object temperature)	
Dust drying	after 45 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 8 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 20 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500	

Further processing of coated pieces

Repainting	after 0,5 hours / room temperature approx. 20 °C.
-------------------	---

Comments

EFD info	Further technical information can be found in the EFD Info. No. 170.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.



UR1955V_HU0061 EFDEDUR-Lackfarbe

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.