



WU1451G_HU0050_CLEARCOAT EFDEDUR-Hydro-Clearcoat

Product description

Product technology	water-thinnable 2C coating
Application area	e.g. in the vehicle construction sector
Application	for exterior use
Substrate	Primer

General product properties

Binder-Base	Acrylic Resin
Colour	colourless
Gloss value	glossy 80-90 GU, Angle 60° DIN EN ISO 2813
Viscosity	Flow time 38-42 sec. 4 mm flow cup DIN 53211
pH-Value	7,5-8,5 DIN 19260
Solid mass	40-45 % after addition of hardener theoretical
Solid content in volume	38-42 % after addition of hardener theoretical
Reference product	The values given refer to the product with the shade WU1451GRA999.
Resistance to storage	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>



WU1451G_HU0050_CLEARCOAT EFDEDUR-Hydro-Clearcoat

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	On blasted steel plate
Structure recommendation	Primer	WE1935MRU124 Mixing ratio 8:1 /HE0041 Dry film thickness 60 µm
Structure recommendation	Top coat	WU1451GRA742 Mixing ratio 5:1 /HU0050 Dry film thickness 40 µm
Structure recommendation	Clearcoat	WU1451GRA999 Mixing ratio 5:1 /HU0050 Dry film thickness 40 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.	
Hardener	HU0050 see technical data sheet	
Mixing ratio	Parts by weight 5:1 Volume parts 4,7:1	
Thinning	demineralised water	
Dry film thickness	must not exceed 60 µm – risk of reaction bubbles.	
Object temperature	10-30 °C, minimum +3 °C above dew point temperature	
Processing conditions	Room temperature 18-22 °C Relative humidity 40-60 %	
Processing time	max. 4 hrs. / 20 °C End of the processing time cannot be detected from gelling. The processing time can decrease at higher temperatures and/or under pressure.	
Airmix spraying	30-60 sec. / 4 mm viscosity cup Nozzle 0,23 mm angle 40° Material pressure 80 bar Atomiser pressure 3 bar	DIN 53211
High pressure spraying	30-50 sec. / 4 mm Flow cup Nozzle 1,5 mm Injection pressure 3 bar	DIN 53211

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510

www.freilacke.de | info@freilacke.de



WU1451G_HU0050_CLEARCOAT EFDEDUR-Hydro-Clearcoat

Rolling/painting	as delivered viscosity	
Material usage	without application loss 105-115 g/m ² layer thickness 40 µm after addition of hardener	theoretical
Oven drying	up to 80 °C possible	
Intermediate drying	60 min. / 20 °C (object temperature)	
Air drying	18-22 °C, 40-60 % relative humidity	
Dust drying	after 60 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 8 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 8 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916, dried-on equipment with org. solvents, e.g. EFD thinner 400424.	

Further processing of coated pieces

Repainting	possible with same quality, dry at the earliest after matting.
-------------------	--

Comments

EFD info	Further technical information can be found in the EFD Info. No. 109 + 111.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.