



WK4003HRU999 FREIOTHERM-KTL-Automotive

Product description

Product technology	cathodic electrocoat paint depositable 2K
Application area	e.g. in the mechanical engineering and plant construction sector
Type of paste	Transparent paste, fully neutralised

General product properties

Binder-Base	Epoxy Resin, modified	
Colour	colourless	
MEQ/s-Value	30-40 mmol/100g	DIN EN ISO 15880
Density	1,0-1,2 g/cm ³	theoretical
Solid mass	34-36 %	theoretical
Resistance to storage	<p>approx. 9 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.
Mixin ratio	Products WK4003HRU999 : WK4997HRU905 Parts by weight 3 : 1
Turn-over	1 Turnover per year To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the ETL tank) must be observed.

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>