



WA4706HL1454

FREIOTHERM-ATL-EcoOne

Product description

Product technology	anodic electrocoat paint depositable 2K	
Application area	e.g. in the functional furniture and storage technology sector	
Application	Single coat system	
Type of paste	Pigment paste, fully neutralised	

General product properties

Binder-Base	Acrylic Resin, modified	
Colour	lenzen grey	
Viscosity	6000-10000 mPa*s	
MEQ-Base-Value	20-28 mg/g	DIN EN ISO 15880
Density	1,29 g/cm ³	theoretical
Solid mass	58-62 %	theoretical
Resistance to storage	<p>approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Gloss value	15-35 GU, Angle 60°	DIN EN ISO 2813
Mixing ratio	Products WA4001:WA4706 Parts by weight 1 : 1	
Recommended coating thickness	3-8 µm	
pH-Value	8,4-9,1	DIN 19260
Cunductance	1400-2400 µS/cm	
Solid mass	14-17 %	DIN EN ISO 3251

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510

www.freilacke.de | info@freilacke.de



WA4706HL1454

FREIOTHERM-ATL-EcoOne

Bath Temperature	24-27 °C
Coating Time	1-10 sec.
Deposition Voltage	100-200 Volts
Turn-over	1 Turnover per year To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the tank) must be observed.

Comments

Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.