

EFDEDUR

HighSolid-Coating UR1984H

- 2-component-polyurethane-finish coat with solvent
- In- and outdoor usage
- For industrial goods, e.g. mechanical engineering
- Good working properties
- Very fast drying
- Good corrosion protection

Technical / Physical Data	Resin/ binder	acryl resin to be hardened with isocyanate
	Colour	acc. to RAL 840 HR other colour shades on request
	Gloss value DIN 67530 and DIN EN ISO 2813	satin mat 25 to 45 geometry 60°
	Original viscosity DIN 53211* without hardener	60 to 80 Sec. / 4 mm cup
	Mixing ratio by weight	8 : 1
	Hardener base	EFDEDUR-Hardener HU0936 polyisocyanate
	Potlife after hardener addition	max. 2 h / 20°C
	Thinner	EFD-Thinner 400018, 400320 or 400500
	Density after hardener addition calculated	1,52 g / ml + / - 0,15
	Solid content after hardener addition calculated	74 % + / - 2
	Solid content in volume after hardener addition calculated	350 ml / kg + / - 20
	Consumption calculated after hardener addition in original viscosity, without application loss	140 to 150 m ² / kg dry film thickness 50 µm see „Special remarks“

Storability Approx. 12 month in original packings at an ambient temperature of 5 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective.

Processing and application

Application

Components are to be mixed homogeneously (e.g. with high-speed mixer).

spraying-highpressure: after hardener addition
 nozzle: 1,6 mm spraying pressure: 3 to 4 bar

Substrates

Steel, non ferrous metals

Pretreatment

The substrate must be free of materials which prevent adhesion, e.g. oil, grease, dust and surfactant. According to the requirements we recommend to apply the suited chemical (e.g. phosphatizing, chromating) or / and mechanical (e.g. shot blasting) pretreatment.

Proposal for a coating system 1

substrate: steel
primer: EFDEDUR-HighSolid-Primer UR1407
top coat: EFDEDUR-HighSolid-Coating UR1984H

Proposal for a coating system 2- as one coat paint (no outdoor usage)

substrate: steel, iron phosphatized
top coat: EFDEDUR-HighSolid-Coating UR1984H

Application temperature

above 10 °C

Drying

air drying at 20°C

dust dry:	after 10 min.	(degree of drying 1/ DIN EN ISO 9117-5)
dry to touch:	after 2 h	(degree of drying 4/ DIN EN ISO 9117-5)
complete dry:	after 7 days	(swinging beam hardness/ DIN EN ISO 1522)
oven drying:	to 100°C possible	(object temperature)

Cleaning of working equipment

EFD-Thinner 400500

Advise for safety protection and protection of health

The usual precautionary measures for ventilation as well as for personal protection are to be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning health protection and environment protection can be read in the corresponding safety data sheet.

Special remarks

Information about Hardener and Thinner

The hardener and the thinner mentioned on page 1 are stated as standard components for this paint system. The standard hardener is also written in the order documents as well as on the label.

Furthermore there are additional hardeners and thinners, which can be used as alternative in case the standard components doesn't meet the requirements. These products are tailor-made e.g. faster or slower hardening.

Hardener are taking influence on the gloss. (see page 1).

Test condition

*Indication of the delivery viscosity according to DIN 53211:

DIN 53211 was withdrawn in October 1996. On request the value is available according to DIN EN ISO 2431.

The statements concerning efficiency and drying depend on colour shade.

The values mentioned in this data sheet are based on UR1984HG1924, bluegrey and hardening with HU0936.

All information is based on a standard climate 20/65 DIN 50014.

For the calculation of the practical consumption loss additions have to be considered. Indications to this are the practical experience and advices given in DIN 53220.

All information are based on our product knowledge and experience. To the application we have no direct influence. For further information please don't hesitate to contact us.

The information mentioned herein are reference values and are not given as specification.