



UR1982M_HU0001 EFDEDUR-Coating

Product description

Product technology	solvent-based 2-component coating	
Property	electrically conductive effect	
Drying	quickly	
Substrate	Primer	

General product properties

Binder-Base	Acrylic Resin	
Colour	All common colour shades	
Gloss visually	matt	
Viscosity	Flow time 35-45 sec., 4 mm flow cup	DIN 53211
Density	1,2-1,35 g/ml after addition of hardener	theoretical
Solid mass	57-61 % after addition of hardener	theoretical
Solid content in volume	39-41 % after addition of hardener	theoretical
Reference product	The specified values refer to the product UR1982MZ1302.	
Resistance to storage	<p>approx. 24 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	On blasted steel plate
	Primer	ER1920M Mixing ratio 20:1 HE0052 Dry film thickness 30-50 µm
	Top coat	UR1982M Mixing ratio 9:1 HU0001 Dry film thickness 30-50 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
Hardener	HU0001	



UR1982M_HU0001 EFDEDUR-Coating

Mixin ratio	Parts by weight 9:1	
Thinning	EFD dilution 400500	
Processing conditions	from 10 °C to 25 °C	
Processing time	max. 2 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.	
High pressure spraying	Set to 25-30 sec / 4 mm flow-cup after adding hardener Nozzle 1,4-1,7 mm Spray pressure 3-4 bar	DIN 53211
Material usage	without application loss 90-120 g/m ² layer thickness 30 µm after addition of hardener	theoretical
Oven drying	up to 80 °C possible (object temperature)	
Air drying	20 °C, 50 % relative humidity	
Dust drying	after 10 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 1,5 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 7 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500	

Comments

EFD info	Further technical information can be found in the EFD Info. No. 170.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.