



WA4000HRU999

FREIOTHERM-ATL-Transparent paste

Product description

Product technology	anodic electrocoat paint depositable 2K	
Application area	e.g. in the functional furniture and storage technology sector	
Type of paste	Transparent paste, fully neutralised	

General product properties

Binder-Base	Acrylic Resin	
Colour	colorless	
MEQ-Base-Value	50-60 mg/g	DIN EN ISO 15880
Density	1-1,1 g/cm ³	theoretical
Solid mass	38-42 %	theoretical
Resistance to storage	<p>approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-improving substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Mixin ratio	Products WA4000:WA4700 Parts by weight 1:1	
Turn-over	1 Turnover per year To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the tank) must be observed.	

Further processing of coated pieces

Repainting	<p>Preparation: Sanding with fine grain size (e.g. 240).</p> <p>Recommendation: Acrylate-based top coat; alkyd-based coatings are not suitable for recoating!</p>	
-------------------	---	--



WA4000HRU999

FREIOTHERM-ATL-Transparent paste

Comments

Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.