



## WU1997M\_HU0208 EFDEDUR-Hydro-Coating

### Product description

<b>Product technology</b>	water-thinnable 2C coating
<b>Application area</b>	e.g. in the vehicle construction sector
<b>Application</b>	for exterior use
<b>Mechanical resistance</b>	good hardness and elasticity
<b>Substrate</b>	Primer

### General product properties

<b>Binder-Base</b>	Acrylic Resin
<b>Colour</b>	All common colour shades
<b>Viscosity</b>	Flow time 30-40 sec. 4 mm flow cup <span style="float: right;">DIN 53211</span>
<b>pH-Value</b>	6,5-7,5 <span style="float: right;">DIN 19260</span>
<b>Solid mass</b>	48-52 % after addition of hardener <span style="float: right;">theoretical</span>
<b>Solid content in volume</b>	37-40 % after addition of hardener <span style="float: right;">theoretical</span>
<b>Reference product</b>	The values given refer to the product with the shade WU1997MRU905.
<b>Resistance to storage</b>	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>



## WU1997M\_HU0208 EFDEDUR-Hydro-Coating

### Application and processing

<b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
<b>Structure recommendation</b>	Substrate	On blasted steel plate
<b>Structure recommendation</b>	Primer	WE1935LRU113 Mixing ratio 8:1/ HE0041 Dry film thickness 60 µm
<b>Structure recommendation</b>	Top coat	WU1997MRU905 Mixing ratio 5,7:1/ HU0208 Dry film thickness 50 µm
<b>Note before use</b>	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.	
<b>Hardener</b>	HU0208 see technical data sheet	
<b>Mixin ratio</b>	Parts by weight 5,7:1 Volume parts 5:1	
<b>Thinning</b>	demineralised water	
<b>Dry film thickness</b>	must not exceed 100 µm – risk of reaction bubbles.	
<b>Object temperature</b>	10-30 °C, minimum +3 °C above dew point temperature	
<b>Processing conditions</b>	Room temperature 18-25 °C Relative humidity 40-60 %	
<b>Processing time</b>	max. 3 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.	
<b>Airless spraying</b>	45-60 sec. / 4 mm viscosity cup Nozzle 0,28 mm angle 40° Material pressure 160 bar	DIN 53211
<b>Airmix spraying</b>	45-60 sec. / 4 mm viscosity cup Nozzle 0,28 mm angle 40° Material pressure 120 bar Atomiser pressure 3 bar	DIN 53211
<b>Material usage</b>	without application loss 170-180 g/m <sup>2</sup> layer thickness 40 µm	theoretical
<b>Air drying</b>	18-22 °C, 40-60 % relative humidity	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6  
78199 Bräunlingen-Döggingen | Deutschland  
+49 77071510

[www.freilacke.de](http://www.freilacke.de) | [info@freilacke.de](mailto:info@freilacke.de)



## WU1997M\_HU0208 EFDEDUR-Hydro-Coating

<b>Dust drying</b>	after 20 minutes (degree of dryness 1)	DIN EN ISO 9117-5
<b>Dry to the touch</b>	after 6 hours (degree of dryness 4)	DIN EN ISO 9117-5
<b>Full drying</b>	after 8 day/s (pendulum damping)	DIN EN ISO 1522
<b>Cleaning of equipment</b>	immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916, dried-on equipment with org. solvents, e.g. EFD thinner 400424.	

### Comments

<b>EFD info</b>	Further technical information can be found in the EFD Info. No. 111 + 510.
<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>