



## ER1912V\_HE0915 FREOPOX-Primer

### Product description

<b>Product technology</b>	solvent-based 2-component coating	
<b>Application area</b>	e.g. in the vehicle construction sector	
<b>Application</b>	suitable as adhesion promoter	
<b>Over-coating capability</b>	"Wet on wet" method	
<b>Corrosion protection</b>	very good	
<b>Substrate</b>	Steel, Stainless steel, Aluminium, Galvanised steel	

### General product properties

<b>Binder-Base</b>	Epoxy resin	
<b>Colour</b>	in accordance with RAL 840 HR other colours on request	
<b>Gloss visually</b>	matt	
<b>Viscosity</b>	2000-2800 mPa*s, spindle 4, 60 revolutions/min.	DIN EN ISO 2555
<b>Density</b>	1,35-1,45 g/ml after addition of hardener	theoretical
<b>Solid mass</b>	67-69 % after addition of hardener	theoretical
<b>Solid content in volume</b>	48-49 % after addition of hardener	theoretical
<b>Reference product</b>	The specified values refer to the product ER1912VRU735.	
<b>Resistance to storage</b>	approx. 24 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

### Application and processing

<b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
<b>Structure recommendation</b>	Substrate	Steel
	Primer	ER1912V Mixing ratio 5:1 HE0052 Dry film thickness 70-90 µm
	Top coat	UR1449G Mixing ratio 7:1 HU0140 Dry film thickness 40-60 µm

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Page 1/3 | Version 0

Revision date: Jul 19, 2024

Print date: Aug 1, 2024

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6  
78199 Bräunlingen-Döggingen | Deutschland  
+49 77071510

[www.freilacke.de](http://www.freilacke.de) | [info@freilacke.de](mailto:info@freilacke.de)



## ER1912V\_HE0915 FREOPOX-Primer

<b>Note before use</b>	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
<b>Hardener</b>	HE0915	
<b>Mixin ratio</b>	Parts by weight 10:1	
	Volume parts 6,32:1	
<b>Thinning</b>	EFD dilution 400424	
<b>Processing conditions</b>	from 10 °C to 25 °C	
<b>Processing time</b>	max. 24 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.	
<b>Airless spraying</b>	50-70 sec. / 4 mm viscosity cup Nozzle 0,58-0,75 mm angle 4° Material pressure 120-150 bar	DIN 53211
<b>High pressure spraying</b>	Set to 30-50 sec / 4 mm flow-cup after adding hardener Nozzle 1,5 mm Spray pressure 3 bar	DIN 53211
<b>Rolling/painting</b>	as delivered viscosity after curing agent addition	
<b>Material usage</b>	without application loss 220-240 g/m <sup>2</sup> layer thickness 80 µm after addition of hardener	theoretical
<b>Oven drying</b>	up to 80 °C possible (object temperature)	
<b>Air drying</b>	20 °C, 50 % relative humidity	
<b>Dust drying</b>	after 25 minutes (degree of dryness 1)	DIN EN ISO 9117-5
<b>Dry to the touch</b>	after 4 hours (degree of dryness 4)	DIN EN ISO 9117-5
<b>Full drying</b>	after 10 day/s (pendulum damping)	DIN EN ISO 1522
<b>Cleaning of equipment</b>	with EFD dilution 400424 within the processing time.	

### Further processing of coated pieces

<b>Repainting</b>	after 20 min. / 20 °C with an intermediate drying time of $\geq 3$ days / 20 °C, recoatability must be tested.
-------------------	---

### Comments

<b>EFD info</b>	Further technical information can be found in the EFD Info. No. 170.
<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.



## ER1912V\_HE0915 FREOPOX-Primer

### Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.