



WL1536M

FREIOPLAST-Hydro-Structure Coating

Product description

Product technology	water-thinnable 1C coating
Application area	e.g. in the vehicle construction sector
Surface	Different structures are possible depending on application and viscosity.
Substrate	Primer

General product properties

Binder-Base	Styrene butadiene dispersion
Colour	All common colour shades
Viscosity	7800-8200 mPa*s, spindle 7, 60 revolutions/min. DIN EN ISO 2555
pH-Value	8,5-8,7 DIN 19260
Solid mass	52-54 % theoretical
Solid content in volume	46-48 % theoretical
Reference product	The values given refer to the product with the shade WL1536MRU611.
Resistance to storage	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>



WL1536M

FREIOPLAST-Hydro-Structure Coating

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	According to customer requirements
Structure recommendation	Primer	ER1912MRU735 Mixing ratio 5:1/ HE0052 Dry film thickness 60 µm
Structure recommendation	Intermediate layer	WL1536MRU611 Dry film thickness 150 µm
Structure recommendation	Top coat	WU1488GS2614 Mixing ratio 3,3:1/ HU0448 Dry film thickness 40 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.	
Thinning	demineralised water	
Object temperature	18-28 °C, minimum +3 °C above dew point temperature	
Processing conditions	Room temperature 18-28 °C Relative humidity 40-60 %	
High pressure spraying	as delivered viscosity nozzle 2 mm spray pressure 5 bar	
Material usage	without application loss 140-150 g/m ² layer thickness 60 µm	theoretical
Oven drying	up to 80 °C possible	
Air drying	18-22 °C, 40-60 % relative humidity	
Dust drying	after 20 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 5 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 14 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916, dried-on equipment with org. solvents, e.g. EFD thinner 400424.	



WL1536M

FREIOPLAST-Hydro-Structure Coating

Further processing of coated pieces

Repainting	possible based on pre-test
-------------------	----------------------------

Comments

EFD info	Further technical information can be found in the EFD Info. No. 111.
-----------------	--

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
----------------------------------	--

Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.
------------------------	--

The information provided here contains reference values and does not constitute a specification.