



UR1407M_HU0936 EFDEDUR-HighSolid-Primer

Product description

Product technology	High-solid coating
Application area	e.g. in the mechanical engineering and plant construction sector
Drying	quickly
Full drying	fast complete drying
Corrosion protection	good
Substrate	Non-ferrous metals, Steel

General product properties

Binder-Base	Alkyd resin		
Colour	in accordance with RAL 840 HR other colours on request		
Gloss value	mat	20-30 GU, Angle 60°	DIN EN ISO 2813
Viscosity	Flow time 100-120 sec. 4 mm flow cup		DIN 53211
Density	1,46-1,76 g/ml after addition of hardener		theoretical
Solid mass	73-77 % after addition of hardener		theoretical
Solid content in volume	320-360 ml/kg		theoretical
Reference product	The specified values refer to the product UR1407MRU735.		
Resistance to storage	approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.		
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.		

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.		
Structure recommendation	Substrate	Steel	
	Primer	UR1407M Mixing ratio 8:1 HU0936 Dry film thickness 50 µm	
	Top coat	UR1984 Coating thickness 50 µm	



UR1407M_HU0936 EFDEDUR-HighSolid-Primer

Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
Hardener	HU0936	
Mixin ratio	Parts by weight 8:1	
Thinning	EFD dilution 400018 EFD dilution 400320 EFD dilution 400500	
Processing conditions	Room temperature 18-24 °C	
Processing time	Max. 90 min. / 23 °C The processing time can decrease at higher temperatures/humidities and/or under pressure.	
High pressure spraying	as delivered viscosity after adding curing agent nozzle 1,6 mm spray pressure 3-4 bar	
Material usage	without application loss 140-150 g/m ² layer thickness 50 µm after addition of hardener	theoretical
Oven drying	up to 100 °C possible	
Dust drying	after 10 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 30 minutes (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 7 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500	

Comments

EFD info	Further technical information can be found in the EFD Info. No. 170+510.	
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.	
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.	