



WA4707HR2629

FREIOTHERM-ATL-Low-Solvent

Product description

Product technology	anodic electrocoat paint depositable 2K	
Application area	e.g. in the functional furniture and storage technology sector	
Application	Primer and single coat system	
Type of paste	Subsequent paste filling, partly neutralised	
Scratch resistance	high scratch resistance	

General product properties

Binder-Base	Acrylic Resin	
Colour	Light grey	
MEQ-Base-Value	11-14 mg/g	DIN EN ISO 15880
Density	1,3-1,6 g/cm ³	theoretical
Solid mass	68-72 %	theoretical
Resistance to storage	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Gloss value	40-50 GU, Angle 60°	DIN EN ISO 2813
Mixin ratio	The mixing ratio is dependent on various factors and is therefore coordinated with the relevant system in cooperation with the application technology department.	
Recommended coating thickness	15-20 µm	
pH-Value	8,2-8,6	DIN 19260
Cunductance	1300-1600 µS/cm	
Solid mass	16-18 %	DIN EN ISO 3251

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de



WA4707HR2629

FREIOTHERM-ATL-Low-Solvent

MEQ-Base-Value 40-50 mg/g

DIN EN ISO 15880

Organic Solvent Content 0,5-1,2 %

Bath Temperature 22-28 °C

Coating Time 60-180 sec.


Deposition Voltage 100-300 Volts

Turn-over 1 Turnover per year

To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the tank) must be observed.

Curing

Recommended object temperature 10 minutes at 170 °C



Objekt Temperatur in °C Object Temperature in °C	160	170	180
Haltezeit Minimum in Minuten Holding time minimum in minutes	20	10	5
Haltezeit Maximum in Minuten Holding time maximum in minutes	30	25	15

Note on greenbake

The coating is suitable for greenbake if you use modified powder coatings for overpainting. The processing company is responsible for ensuring that the coating is fully cured. The complete curing of the coating must be checked by means of additional analytical and resistance tests using representative original parts under production conditions. Please do not hesitate to contact us if you require consultation.



WA4707HR2629

FREIOTHERM-ATL-Low-Solvent

Note on curing

Coloured area = stoving conditions with good end properties

The displayed baking conditions are based on results from laboratory tests and therefore merely serve as a guideline when configuring the processing company's coating systems. The processing company is responsible for ensuring that the coating is fully cured. The complete curing of the coating must be checked by means of additional analytical and resistance tests using representative original parts under production conditions. Please do not hesitate to contact us if you require consultation.



WA4707HR2629

FREIOTHERM-ATL-Low-Solvent

Mechanical tests

Test substrate	on iron phosphating	
Cross-cut-test	Gt 0	DIN EN ISO 2409
Cupping test	4 mm	DIN EN ISO 1520
Mandrel bending test cylindrical	8 mm	DIN EN ISO 1519
Pencil Hardness	3 H	DIN EN ISO 15184
Buchholz penetration test	1,0 mm	DIN EN ISO 2815

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>