



KP1616M

FREIOPLAST-ESD-Peel-off Coating

Product description

Product technology	Solvent-based air-drying coating	
Property	electrostatic dissipative (ESD)	
Drying	quickly	
Full drying	fast complete drying	
Mechanical resistance	good flexibility	
Substrate	Plastic, not defined in more detail, Non-ferrous metals, Steel, mineral	

General product properties

Binder-Base	Polyvinylbutyral	
Colour	in accordance with RAL 840 HR other colours on request	
Gloss visually	matt	
Viscosity	Flow time 80-120 sec., 4 mm flow cup	DIN 53211
Density	1,01-1,11 g/ml	theoretical
Solid mass	39-43 %	theoretical
Solid content in volume	23-33 %	theoretical
Reference product	The specified values refer to the product KP1616MRU743.	
Resistance to storage	approx. 12 month in original packagings at an ambient temperature of 18 to 25 °C. Protect from frost. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues.	
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
Thinning	EFD dilution 400906 (schnell) EFD dilution 400500 (langsam)	
Processing conditions	from 10 °C to 25 °C	
Rolling/painting	as delivered viscosity	
Material usage	without application loss 180-190 g/m ² layer thickness 50 µm	theoretical
Oven drying	up to 100 °C possible (object temperature)	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Page 1/2 | Version 1

Revision date: Jan 16, 2025

Print date: Jan 16, 2025

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510

www.freilacke.de | info@freilacke.de



KP1616M

FREIOPLAST-ESD-Peel-off Coating

Air drying	20 °C, 50 % relative humidity	
Dust drying	after 10 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 2 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 18 hours (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500	

Comments

EFD info	Further technical information can be found in the EFD Info. No. 170.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>