Technical Data Sheet

FreiLacke

WA4794HL1820

FREIOTHERM-ATL-CorrosionResist

Product description

Product technology	anodic electrocoat paint depositable 1K
Application area	e.g. in the functional furniture and storage technology sector
Application	Single coat system
Type of paste	Subsequent paste filling, partly neutralised
Corrosion protection	good

General product properties

Binder-Base	Acrylic Resin, modified	
Colour	lenzen grey jumbo	
Viscosity	3000 - 8000 mPa*s	
MEQ-Base-Value	35 - 42 mg/g	DIN EN ISO 15880
Density	1,1 - 1,3 g/cm³	theoretical
Solid mass	63 - 67 %	theoretical
Resistance to storage	approx. 12 month in original packagings at an ambient temperature of 5 to 30 °C. Protect from frost. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Gloss value	15 - 35 GU, Angle 60°	DIN EN ISO 2813
Recommended coating thickness	3 - 8 µm	
pH-Value	8,5 - 9,5	DIN 19260
Cunductance	1400 - 1700 µS/cm	
Solid mass	14 - 17 %	DIN EN ISO 3251
MEQ-Base-Value	55 - 80 mg/g	DIN EN ISO 15880
Organic Solvent Content	1,0 - 3,5 %	
Bath Temperature	24 - 27 °C	
Coating Time	1 - 10 sec.	

Our technical data sheets are to provide you with advice based on our latest state of knowledge.
This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.
The sale of our products is in accordance with our terms of business, delivery and payment.

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de

WA4794HL1820

FREIOTHERM-ATL-CorrosionResist

Deposition Voltage	100 - 200 Volts
Turn-over	1 Turnover per year To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the tank) must be observed.

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.

Our technical data sheets are to provide you with advice based on our latest state of knowledge.
This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.
The sale of our products is in accordance with our terms of business, delivery and payment.

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de