



BD7130M DURELASTIC-Top Coat

Product description

Product technology	Styrene-based top coat
Substrate	GRP (glassfibre reinforced plastic)

General product properties

Binder-Base	unsaturated polyester resin, styrene containing
Colour	in accordance with RAL 840 HR other colours on request
Gloss visually	matt
Viscosity	5000 - 6000 mPa*s
Density	1,3 g/ml theoretical
Resistance to storage	approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application. As the time in storage increases, the gelling and curing times can change. The original gelling time can be adjusted by adding accelerators (e.g. BD7550).

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues.
Note before use	Prior to use, stir slowly and well without letting air in or mix components homogeneously.
Mixin ratio	+ 2 % Durelastic curing agent (MEKP 50) HD0625
Thinning	EFD dilution 3-5 % EFD dilution 400900
Processing conditions	During processing, a room, material and mould temperature of [Variable] °C must be guaranteed in order to prevent hardening problems and cracking.
Processing time	max. 15 - 20 min. / 20 °C With the addition of 2 % 0
painting	as delivered viscosity
Rolling	as delivered viscosity
Material usage	500 g/m ² mean test layer thickness theoretical
Cleaning of equipment	with EFD cleaning agent 400909 oder 400906 within the processing time.

Comments

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Page 1/2 | Version 0

Revision date: Aug 7, 2024

Print date: Aug 7, 2024

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510

www.freilacke.de | info@freilacke.de



BD7130M DURELASTIC-Top Coat

Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.