



BD7528X

DURELASTIC-Carbon Black Paste

Product description

Property	colour intensive
Pigment content	highly concentrated

General product properties

Binder-Base	Unsaturated, styrene-free polyester resin	
Viscosity	<4000 mPa*s, spindle 4, 20 revolutions/min.	DIN EN ISO 2555
Density	1,3 +/- 0,1 g/ml	theoretical
Resistance to storage	approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Application	as delivered viscosity 2 - 5 % for colouring resins 10 - 15 % for colouring cover layer resins
Cleaning of equipment	EFD cleaning agent 400906

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.