



WU1963M_HU0150 EFDEDUR-Hydro-Bonded Coating

Product description

Product technology	water-thinnable 2C coating		
Application area	e.g. in the vehicle construction sector		
Application	for exterior use		
Mechanical resistance	good		
Substrate	Steel, Primer		

General product properties

Binder-Base	Acrylic Resin		
Colour	All common colour shades		
Viscosity	Flow time 40-45 sec. 4 mm flow cup		DIN 53211
pH-Value	8,0-8,8		DIN 19260
Solid mass	50-54 % after addition of hardener		theoretical
Solid content in volume	42-45 % after addition of hardener		theoretical
Reference product	The values given refer to the product with the shade WU1963MRU905.		
Resistance to storage	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>		

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.		
Structure recommendation	Substrate	According to customer requirements	
	Top coat	WU1963MRU905 Mixing ratio 6:1/ HU0150 Dry film thickness 40 µm	



WU1963M_HU0150 EFDEDUR-Hydro-Bonded Coating

Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.	
Hardener	HU0150 see technical data sheet	
Mixin ratio	Parts by weight 6:1 Volume parts 5,8:1	
Thinning	demineralised water	
Dry film thickness	must not exceed 70 µm – risk of reaction bubbles.	
Object temperature	10-30 °C, minimum +3 °C above dew point temperature	
Processing conditions	Room temperature 18-22 °C Relative humidity 40-60 %	
Processing time	max. 4 hrs. / 20 °C End of the processing time cannot be detected from gelling. The processing time can decrease at higher temperatures and/or under pressure.	
Airmix spraying	30-40 sec. / 4 mm viscosity cup Nozzle 0,23 mm angle 30° Material pressure 80 bar Atomiser pressure 2-4 bar	DIN 53211
High pressure spraying	30-40 sec. / 4 mm Flow cup Nozzle 1,5 mm Injection pressure 3 bar	DIN 53211
Material usage	without application loss 100-110 g/m ² layer thickness 40 µm after addition of hardener	theoretical
Oven drying	up to 80 °C possible	
Air drying	18-22 °C, 40-60 % relative humidity	
Dust drying	after 30 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 8 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 8 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916, dried-on equipment with org. solvents, e.g. EFD thinner 400424. Do not mix curing agent with water! The cleaning must be carried out with organic solvents.	

Comments

EFD info	Further technical information can be found in the EFD Info. No. 111 + 510.	
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.	



WU1963M_HU0150 EFDEDUR-Hydro-Bonded Coating

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.