Technical Data Sheet





BD7508V DURELASTIC-Pigment paste

Product description

| Property | colour intensive |
|---------------------------------|---------------------|
| Resistance to light and weather | good |
| Pigment content | highly concentrated |

General product properties

| Binder-Base | Unsaturated, styrene-free polyester resin | |
|-----------------------|--|-----------------|
| Viscosity | 7000 mPa*s, spindle 0, 0 revolutions/min. | DIN EN ISO 2555 |
| Density | 2,0 g/cm ³ depending on the shade | theoretical |
| Solid mass | 95 - 97 % | theoretical |
| Resistance to storage | approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time. | |
| | The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application. | |

Application and processing

| Note before use | Carry out pretesting, as pigments may delay or extend pot lives depending on the colour shade. |
|-----------------------|--|
| Application | as delivered viscosity 2 - 5 % for colouring resins |
| Cleaning of equipment | EFD cleaning agent 400906 |
| | |

Comments

| Work-and Healthprotection | The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet. |
|------------------------------|--|
| Test conditions | All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. |
| | The information provided here contains reference values and does not constitute a specification. |

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.

The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG