



GS1954H_HU0036

EFDEDUR-HighSolid-Structure Coating

Product description

Product technology	solvent-based 2-component coating
Surface	coarse structure
Application	For interior and exterior applications
Property	Silicone-free
Drying	quickly
Full drying	fast complete drying
Substrate	Plastic, not defined in more detail, Non-ferrous metals, Steel

General product properties

Binder-Base	Acrylic Resin		
Colour	in accordance with RAL 840 HR other colours on request		
Gloss value	Satin gloss	18-35 GU, Angle 60° The degree of gloss is strongly dependent on the structure. The given value refers to a smooth, weakly structured surface.	DIN EN ISO 2813
Viscosity	3000-8000 mPa*s, spindle 6, 60 revolutions/min.		DIN EN ISO 2555
Density	1,42-1,62 g/ml after addition of hardener		theoretical
Solid mass	73-77 % after addition of hardener		theoretical
Solid content in volume	355-395 ml/kg after addition of hardener		theoretical
Reference product	The specified values refer to the product GS1954HRA208.		
Resistance to storage	approx. 24 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.		



GS1954H_HU0036

EFDEDUR-HighSolid-Structure Coating

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	Non-ferrous metals e.g. aluminium
	Primer	ER1912M Mixing ratio 5:1 HE0052 Dry film thickness 70-90 µm
	Top coat	GS1954H Mixing ratio 9:1 HU0036 Dry film thickness 80-120 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
	Steel:	Priming is not absolutely essential.
	Non-ferrous metals:	A primer is absolutely essential.
	Plastic:	A primer is absolutely essential.
Hardener	HU0036	
Mixin ratio	Parts by weight 9:1	
Thinning	EFD dilution 400320	
	EFD dilution 400500	
Processing conditions	from 10 °C to 25 °C	
Processing time	max. 2 hrs. / 20 °C	
	The processing time can decrease at higher temperatures and/or under pressure.	



GS1954H_HU0036

EFDEDUR-HighSolid-Structure Coating

High pressure spraying

Following the addition of the curing agent, set the processing viscosity in accordance with the respective application process. Depending on the desired texture, the application takes place in one (self-forming texture) or in two operations (sprinkle effect):

1.) Self-forming texture (one operation)

e.g. Sata jet® Nozzle 1,5-2,0 mm

Spray pressure 3-5 bar

Cross coats 1-2

2.) Sprinkle effect (two operations A + B)

e.g. Sata jet® Nozzle 1,5-2,0 mm

Cross coats 1-2

A) Spray pressure 3-5 bar, smooth pre-spraying

following the drying of the coating surface (approx. 30 min. / 20°C)

B) Sprinkle the desired texture using reduced spray pressure

Spray pressure 0,5-2,0 bar

By changing the spray pressure, nozzle diameter, coating viscosity, spray guns and system setting, different surface textures can be achieved. Any wearing of the nozzles and system must be taken into account.

Additional application options must be tested.

Rolling/painting

as delivered viscosity after curing agent addition

Electrostatic

possible, system-specific

Material usage

without application loss 245-285 g/m²

theoretical

layer thickness 80-120 µm after addition of hardener

Oven drying

up to 100 °C possible (object temperature)

Air drying

20 °C, 50 % relative humidity

Dust drying

after 30 minutes (degree of dryness 1)

DIN EN ISO 9117-5

Dry to the touch

after 2 hours (degree of dryness 4)

DIN EN ISO 9117-5

Full drying

after 8 day/s (pendulum damping)

DIN EN ISO 1522

Cleaning of equipment

EFD dilution 400500

Comments

Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.