



FREIOTHERM-Powder Coating


PP5205A

Characteristics	<ul style="list-style-type: none"> ■ Powder coating for decorative use on exteriors ■ Application, e.g. in the vehicle construction sector ■ high glossy, smooth ■ Smooth to apply ■ Good light and weather resistance ■ Good mechanical resistance and surface hardness 												
System Coating	<ul style="list-style-type: none"> ■ System Liquid Coating <p>For various applications, there are coatings available, whose optical appearance regarding colour, gloss degree and surface is in optimum balance.</p>												
Technical / Physical Data	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 30%;">■ Binder-Base</td> <td>polyester resin</td> </tr> <tr> <td>■ Colour</td> <td>all common colour shades</td> </tr> <tr> <td>■ Gloss value <small>DIN EN ISO 2813</small></td> <td>high glossy >85 geometry 60°</td> </tr> <tr> <td>■ Test layer thickness</td> <td>80 µm by colour leuchtenweiß</td> </tr> <tr> <td>■ Density <small>calculated</small></td> <td>1,2-1,7 g/cm³ colour-dependent</td> </tr> <tr> <td>■ Material usage</td> <td>0,12 kg/m² with 80 µm mean test layer thickness</td> </tr> </table>	■ Binder-Base	polyester resin	■ Colour	all common colour shades	■ Gloss value <small>DIN EN ISO 2813</small>	high glossy >85 geometry 60°	■ Test layer thickness	80 µm by colour leuchtenweiß	■ Density <small>calculated</small>	1,2-1,7 g/cm ³ colour-dependent	■ Material usage	0,12 kg/m ² with 80 µm mean test layer thickness
■ Binder-Base	polyester resin												
■ Colour	all common colour shades												
■ Gloss value <small>DIN EN ISO 2813</small>	high glossy >85 geometry 60°												
■ Test layer thickness	80 µm by colour leuchtenweiß												
■ Density <small>calculated</small>	1,2-1,7 g/cm ³ colour-dependent												
■ Material usage	0,12 kg/m ² with 80 µm mean test layer thickness												
Mechanical Test on steel panel ST 1405	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 30%;">■ Cross-cut-test <small>DIN EN ISO 2409</small></td> <td>Gt 0</td> </tr> <tr> <td>■ Erichsen index <small>DIN EN ISO 1520</small></td> <td>>4 mm</td> </tr> <tr> <td>■ Impact-Test <small>DIN EN ISO 6272-1</small></td> <td>80 kg cm (front)</td> </tr> <tr> <td>■ Buchholz penetration test <small>DIN EN ISO 2815</small></td> <td>< 1,2 mm</td> </tr> </table>	■ Cross-cut-test <small>DIN EN ISO 2409</small>	Gt 0	■ Erichsen index <small>DIN EN ISO 1520</small>	>4 mm	■ Impact-Test <small>DIN EN ISO 6272-1</small>	80 kg cm (front)	■ Buchholz penetration test <small>DIN EN ISO 2815</small>	< 1,2 mm				
■ Cross-cut-test <small>DIN EN ISO 2409</small>	Gt 0												
■ Erichsen index <small>DIN EN ISO 1520</small>	>4 mm												
■ Impact-Test <small>DIN EN ISO 6272-1</small>	80 kg cm (front)												
■ Buchholz penetration test <small>DIN EN ISO 2815</small>	< 1,2 mm												
Resistance Test	<ul style="list-style-type: none"> ■ on zinc phosphatized steel plate <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 30%;">■ Condensate constant climate <small>DIN EN ISO 6270-2 (CH)</small></td> <td>1000 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8</td> </tr> <tr> <td>■ Salt spray test (NSS) <small>DIN EN ISO 9227</small></td> <td>500 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8</td> </tr> <tr> <td>■ Chemical resistance</td> <td>Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.</td> </tr> </table>	■ Condensate constant climate <small>DIN EN ISO 6270-2 (CH)</small>	1000 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8	■ Salt spray test (NSS) <small>DIN EN ISO 9227</small>	500 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8	■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.						
■ Condensate constant climate <small>DIN EN ISO 6270-2 (CH)</small>	1000 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8												
■ Salt spray test (NSS) <small>DIN EN ISO 9227</small>	500 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8												
■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.												
Processing and application Dependent on plant and buildings	<ul style="list-style-type: none"> ■ Processing / Loading Corona, Tribo ■ Pretreatment The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. If requirements are more demanding than this, we recommend appropriate levels of phosphatizing or chromating. 												



FREIOTHERM-Powder Coating

PP5205A

	<ul style="list-style-type: none"> ■ Touch-up coating: on enquiry ■ Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<p>Curing</p>	<ul style="list-style-type: none"> ■ Object temperature Recommended baking temperature 10 min./180 °C Baking window tested in colour shade leuchtenweiß green cross-hatching = baking conditions with good final properties 
<p>Resistance to storage</p>	<ul style="list-style-type: none"> ■ Approx. 36 month in original packagings at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
<p>Specific comments</p>	<ul style="list-style-type: none"> ■ Protective screening: 160 µm ■ Compatibility with other powder coatings: Needs to be checked ■ Test conditions All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.