


# FREOPOX-Hydro-Grundierung

## WE1986M/HE0132

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>■ Water-thinnable 2C coating</li> <li>■ Application, e.g. in the vehicle construction sector</li> <li>■ Good adhesion to steel and non-ferrous metals</li> <li>■ Electrically conductive effect</li> </ul>																																		
<b>Technical / Physical Data</b>	<table border="1"> <tr> <td>■ Binder-Base</td> <td>Combination of acrylate/amino resin</td> </tr> <tr> <td>■ Colour</td> <td>All common colour shades</td> </tr> <tr> <td>■ Gloss value <small>visual</small></td> <td>mat</td> </tr> <tr> <td>■ Viscosity</td> <td>1800-3000 mPa.s/ Spindle 5 60 revolution/ min.</td> </tr> <tr> <td>■ Hardener</td> <td>HE0132 See technical data sheet</td> </tr> <tr> <td>■ Mixing ratio</td> <td>Parts by weight 2:1</td> </tr> <tr> <td>■ Mixing ratio</td> <td>Parts by volume 1,55:1</td> </tr> <tr> <td>■ Thinner</td> <td>demineralised water</td> </tr> <tr> <td>■ pH-Value</td> <td>8-9</td> </tr> <tr> <td>■ Density <small>calculated</small></td> <td>1,33-1,53 g/ml</td> </tr> <tr> <td>■ Density <small>calculated</small></td> <td>1,22-1,42 g/ml after adding hardener</td> </tr> <tr> <td>■ Solid Mass <small>calculated</small></td> <td>56,6-60,6 %</td> </tr> <tr> <td>■ Solid Mass <small>calculated</small></td> <td>54,8-58,8 % after adding hardener</td> </tr> <tr> <td>■ Solid content in volume <small>calculated</small></td> <td>260-300 ml/kg</td> </tr> <tr> <td>■ Solid content in volume <small>calculated</small></td> <td>320-340 ml/kg after adding hardener</td> </tr> <tr> <td>■ Material usage <small>theoretical, without application loss</small></td> <td>170-190 g/m<sup>2</sup>, Layer thickness 60 µm after adding hardener</td> </tr> <tr> <td>■ Reference colour of the specified values</td> <td>Colour of WE1900MRU905</td> </tr> </table>	■ Binder-Base	Combination of acrylate/amino resin	■ Colour	All common colour shades	■ Gloss value <small>visual</small>	mat	■ Viscosity	1800-3000 mPa.s/ Spindle 5 60 revolution/ min.	■ Hardener	HE0132 See technical data sheet	■ Mixing ratio	Parts by weight 2:1	■ Mixing ratio	Parts by volume 1,55:1	■ Thinner	demineralised water	■ pH-Value	8-9	■ Density <small>calculated</small>	1,33-1,53 g/ml	■ Density <small>calculated</small>	1,22-1,42 g/ml after adding hardener	■ Solid Mass <small>calculated</small>	56,6-60,6 %	■ Solid Mass <small>calculated</small>	54,8-58,8 % after adding hardener	■ Solid content in volume <small>calculated</small>	260-300 ml/kg	■ Solid content in volume <small>calculated</small>	320-340 ml/kg after adding hardener	■ Material usage <small>theoretical, without application loss</small>	170-190 g/m <sup>2</sup> , Layer thickness 60 µm after adding hardener	■ Reference colour of the specified values	Colour of WE1900MRU905
■ Binder-Base	Combination of acrylate/amino resin																																		
■ Colour	All common colour shades																																		
■ Gloss value <small>visual</small>	mat																																		
■ Viscosity	1800-3000 mPa.s/ Spindle 5 60 revolution/ min.																																		
■ Hardener	HE0132 See technical data sheet																																		
■ Mixing ratio	Parts by weight 2:1																																		
■ Mixing ratio	Parts by volume 1,55:1																																		
■ Thinner	demineralised water																																		
■ pH-Value	8-9																																		
■ Density <small>calculated</small>	1,33-1,53 g/ml																																		
■ Density <small>calculated</small>	1,22-1,42 g/ml after adding hardener																																		
■ Solid Mass <small>calculated</small>	56,6-60,6 %																																		
■ Solid Mass <small>calculated</small>	54,8-58,8 % after adding hardener																																		
■ Solid content in volume <small>calculated</small>	260-300 ml/kg																																		
■ Solid content in volume <small>calculated</small>	320-340 ml/kg after adding hardener																																		
■ Material usage <small>theoretical, without application loss</small>	170-190 g/m <sup>2</sup> , Layer thickness 60 µm after adding hardener																																		
■ Reference colour of the specified values	Colour of WE1900MRU905																																		
<b>Substrate</b>	<ul style="list-style-type: none"> <li>■ Primer</li> </ul>																																		
<b>Pretreatment</b>	<ul style="list-style-type: none"> <li>■ The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. For more stringent requirements, we recommend: for corrosion protection - e.g. phosphating for adhesion - e.g. blasting, pickling, sanding</li> </ul>																																		
<b>Structure recommendation</b>	<table border="1"> <tr> <td>■ Substrate</td> <td>on blasted steel plate</td> </tr> <tr> <td>■ Primer</td> <td>WE1914MRU115</td> </tr> </table>	■ Substrate	on blasted steel plate	■ Primer	WE1914MRU115																														
■ Substrate	on blasted steel plate																																		
■ Primer	WE1914MRU115																																		


Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



**FREOPOX-Hydro-Grundierung**  
WE1986M/HE0132

<b>Processing and application</b>		Mixing ratio 8:1/ HE0181 Dry film thickness 60 µm
	■ Top coat	WE1900MRU905 Mixing ratio 2:1/ HE0170 Dry film thickness 40 µm
	■ Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. Dry film thickness must not exceed µm - risk of reaction bubbles.	
	■ Object temperature	15-30 °C
	■ Processing conditions	Room temperature 16-25 °C Relative humidity 40-70 %
	■ Processing time	max. 3 hrs./ 20 °C End of the processing time cannot be detected from gelling. The processing time can decrease at higher temperatures and/or under pressure.
	■ Airless spraying	as delivered viscosity Nozzle 0,33 mm angle 30° Material pressure 130 bar
	■ Airmix spraying	as delivered viscosity Nozzle 0,33 mm Angle 30° Material pressure 120 bar Atomiser pressure 4
	■ High pressure spraying	as delivered viscosity Nozzle: 1,7 mm Spray pressure 3 bar
	■ Over-coating capability	possible with same quality, dry at the earliest after matting
■ Cleaning of equipment	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424.	
	■ <b>Health &amp; Safety at Work guidelines</b> The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.	
<b>Curing</b>	■ Air drying	at 20°C, 50% relative humidity with air movement
	■ Dust drying	after 15 min. (degree of drying 1/ DIN EN ISO 9117-5)
	■ Dry to the touch	after 3 hrs. (degree of drying 4/ DIN EN ISO 9117-5)
	■ Full drying	after 7 days (pendulum damping/DIN EN ISO 1522)
	■ Oven drying	possible to 70°C
<b>Resistance to storage</b>	■	Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.
		The minimum storage stability of each batch is stated on the product label. The

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



**FREOPOX-Hydro-Grundierung**  
WE1986M/HE0132

	<p>material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>
<b>Specific comments</b>	<ul style="list-style-type: none"> <li>■ <b>Approval</b> available - on request</li> <hr/> <li>■ <b>EFD-info</b> Refer to the EFD information for further technical information. Nr. 111 + 510</li> <hr/> <li>■ <b>Test conditions</b> All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</li> </ul> <p>The information provided here contains reference values and does not constitute a specification.</p>