



ER1920M_HE0915 FREOPOX-Zinc Dust Primer

Product description

Product technology	solvent-based 2-component coating
Application area	e.g. in the construction and sanitary sector
Over-coating capability	"Wet on wet" method
Content	Zinc dust proportion in dry film approx. 90 %
Corrosion protection	very good
Substrate	Steel, Steel, blasted

General product properties

Binder-Base	Epoxy resin	
Colour	Squirrel grey	
Gloss visually	matt	
Viscosity	Flow time 50-80 sec., 4 mm flow cup	DIN 53211
Density	2,65-2,85 g/ml after addition of hardener	theoretical
Solid mass	86-88 % after addition of hardener	theoretical
Solid content in volume	55-59 % after addition of hardener	theoretical
Reference product	The specified values refer to the product ER1920MRU700.	
Resistance to storage	approx. 9 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.
---------------------	---



ER1920M_HE0915 FREOPOX-Zinc Dust Primer

Structure recommendation	Substrate	Steel blasted to Sa 2.5
	Primer	ER1920M Mixing ratio 30:1 HE0195 Dry film thickness 30-50 µm
	Intermediate layer	ER1912M Mixing ratio 5:1 HE0052 Dry film thickness 70-90 µm
	Top coat	UR1044H Mixing ratio 10:1 HU0400 Dry film thickness 40-60 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
Hardener	HE0915	
Mixin ratio	Parts by weight 30:1	
Thinning	EFD dilution 400424	
Processing conditions	from 10 °C to 25 °C	
Processing time	max. 12 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.	
Airless spraying	as delivered viscosity after curing agent addition	
High pressure spraying	as delivered viscosity after adding curing agent nozzle 1,6-2,0 mm spray pressure 2-4 bar	
Material usage	without application loss 140-150 g/m² layer thickness 30 µm after addition of hardener	theoretical
Oven drying	up to 80 °C possible (object temperature)	
Air drying	20 °C, 50 % relative humidity	
Dust drying	after 10 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 2-3 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 10 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	with EFD dilution 400424 within the processing time.	



ER1920M_HE0915 FREOPOX-Zinc Dust Primer

Further processing of coated pieces

Repainting	after 10 min. / 20 °C with an intermediate drying time of ≥ 3 days / 20 °C, recoatability must be tested.
-------------------	---

Comments

Alternative hardener	for rolling HE0052
EFD info	Further technical information can be found in the EFD Info. No. 170.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.