



WK4807HC1711 FREIOTHERM-KTL-Acrylate

Product description

Product technology	cathodic electrocoat paint depositable 2K
Application area	e.g. in the job coater sector
Application	Single coat system
Type of paste	Pigment paste, fully neutralised
Scratch resistance	high scratch resistance
Resistance to light and weather	very good

General product properties

Binder-Base	Acrylic Resin, modified	
Colour	Blum black brown	
Viscosity	4000 - 8000 mPa*s	
Density	1,15 - 1,25 g/cm³	theoretical
Solid mass	63-67 %	theoretical
Resistance to storage	approx. 9 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Gloss value	20-40 GU, Angle 60°	DIN EN ISO 2813
Recommended coating thickness	10 - 20 µm	
pH-Value	4,2 - 4,7	DIN 19260
Cunductance	900-1400 µS/cm	
Solid mass	15-19 %	DIN EN ISO 3251
Organic Solvent Content	2-6 %	
Bath Temperature	28-32 °C	
Coating Time	40-120 sec.	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Page 1/2 | Version 1

Revision date: Jul 17, 2025

Print date: Jul 18, 2025

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de



WK4807HC1711 FREIOTHERM-KTL-Acrylate

Deposition Voltage

70-170 Volts

Turn-over

1 Turnover per year

To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the tank) must be observed.

Comments

Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.