



## BD7781XRU999 DURELASTIC-UP-Resin

### General product properties

<b>Binder-Base</b>	unsaturated polyester resin, styrene containing	
<b>Colour</b>	colorless	
<b>Viscosity</b>	550 - 750 mPa*s	
<b>Density</b>	1,1 +/- 0,1 g/ml	theoretical
<b>Solid mass</b>	63 - 67 %	theoretical
<b>Resistance to storage</b>	<p>approx. 6 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p> <p>As the time in storage increases, the gelling and curing times can change. The original gelling time can be adjusted by adding accelerators ( e.g. BD7550 ).</p>	

### Application and processing

<b>Note before use</b>	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
<b>Mixin ratio</b>	Resin : Accelerator : Hardener Parts by weight 100 : 0,2-0,5 : 2	
<b>Thinning</b>	EFD dilution 400900	
<b>Processing conditions</b>	During processing, a room, material and mould temperature of [Variable] °C must be guaranteed in order to prevent hardening problems and cracking.	
<b>Processing time</b>	max. 6 - 8 min. / 20 °C With the addition of 0,5 % BD7550	
<b>Cleaning of equipment</b>	with EFD cleaning agent 400906 within the processing time.	



## BD7781XRU999 DURELASTIC-UP-Resin

### Mechanical tests

<b>mechanical properties</b>	Elongation at break	> 60 %	DIN EN ISO 527-2
	HDT	< 30 °C	DIN EN ISO 75-2
	Bending strength	35 MPa	DIN EN ISO 178
This information refers to the cured, unreinforced pure resin.			

### Comments

<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.