



ER1912M_HE0052 FREOPOX-Primer

Product description

Product technology	solvent-based 2-component coating	
Application area	e.g. in the vehicle construction sector	
Application	suitable as adhesion promoter	
Over-coating capability	"Wet on wet" method	
Corrosion protection	very good	
Substrate	Steel, Stainless steel, Aluminium, Galvanised steel	

General product properties

Binder-Base	Epoxy resin	
Colour	in accordance with RAL 840 HR other colours on request	
Gloss visually	matt	
Viscosity	1300-2300 mPa*s, spindle 4, 60 revolutions/min.	DIN EN ISO 2555
Density	1,25-1,45 g/ml after addition of hardener	theoretical
Solid mass	59-63 % after addition of hardener	theoretical
Solid content in volume	35-45 % after addition of hardener	theoretical
Reference product	The specified values refer to the product ER1912MRU735.	
Resistance to storage	approx. 24 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	Steel
	Primer	ER1912M Mixing ratio 5:1 HE0052 Dry film thickness 70-90 µm
	Top coat	UR1449G Mixing ratio 7:1 HU0140 Dry film thickness 40-60 µm

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Page 1/2 | Version 2

Revision date: Aug 16, 2024

Print date: Aug 19, 2024

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510

www.freilacke.de | info@freilacke.de



ER1912M_HE0052 FREOPOX-Primer

Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).	
Hardener	HE0052	
Mixin ratio	Parts by weight 5:1	
	Volume parts 3,08:1	
Thinning	EFD dilution 400424	
Processing conditions	from 10 °C to 25 °C	
Processing time	max. 24 hrs. / 20 °C	
	The processing time can decrease at higher temperatures and/or under pressure.	
Airless spraying	as delivered viscosity after curing agent addition	
High pressure spraying	as delivered viscosity after adding curing agent	
Rolling/painting	as delivered viscosity after curing agent addition	
Material usage	without application loss 255-265 g/m ²	theoretical
	layer thickness 80 µm after addition of hardener	
Oven drying	up to 80 °C possible (object temperature)	
Air drying	20 °C, 50 % relative humidity	
Dust drying	after 25 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 4 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 10 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	with EFD dilution 400424 within the processing time.	

Further processing of coated pieces

Repainting	after 20 min. / 20 °C with an intermediate drying time of \geq 3 days / 20 °C, recoatability must be tested.
-------------------	---

Comments

Alternative hardener	for rolling	10:1 HE0915
	for faster drying	5:1 HE0168
EFD info	Further technical information can be found in the EFD Info. No. 170.	
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.	
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.	
	The information provided here contains reference values and does not constitute a specification.	