





## WU1458G\_HU0448 EFDEDUR-Hydro-Coating

### Application and processing

<b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
<b>Structure recommendation</b>	Substrate	KTL primed
<b>Note before use</b>	Top coat WU1458GB2364 Mixing ratio 6:1/ HU0448 Dry film thickness $\mu\text{m}$	
<b>Hardener</b>	HU0448 see technical data sheet	
<b>Mixin ratio</b>	Parts by weight 6:1 Volume parts 5:1	
<b>Thinning</b>	demineralised water	
<b>Dry film thickness</b>	must not exceed 80 $\mu\text{m}$ – risk of reaction bubbles.	
<b>Object temperature</b>	10-30 °C, minimum +3 °C above dew point temperature	
<b>Processing conditions</b>	Room temperature 18-22 °C Relative humidity 40-60 %	
<b>Processing time</b>	max. 4 hrs. / 20 °C End of the processing time cannot be detected from gelling. The processing time can decrease at higher temperatures and/or under pressure.	
<b>Airmix spraying</b>	30-40 sec. / 4 mm viscosity cup Nozzle 0,23 mm angle 30° Material pressure 80 bar Atomiser pressure 3 bar	DIN 53211
<b>High pressure spraying</b>	30-40 sec. / 4 mm Flow cup Nozzle 1,5 mm Injection pressure 3 bar	DIN 53211
<b>Rolling/painting</b>	as delivered viscosity	
<b>Material usage</b>	without application loss 110-130 g/m <sup>2</sup> layer thickness 40 $\mu\text{m}$ after addition of hardener	theoretical
<b>Oven drying</b>	up to 80 °C possible	
<b>Air drying</b>	18-22 °C, 40-60 % relative humidity	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Page 2/3 | Version 0

Revision date: Apr 19, 2024

Print date: Jun 6, 2024

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6  
78199 Bräunlingen-Döggingen | Deutschland  
+49 77071510

[www.freilacke.de](http://www.freilacke.de) | [info@freilacke.de](mailto:info@freilacke.de)



## WU1458G\_HU0448 EFDEDUR-Hydro-Coating

<b>Dust drying</b>	after 30 minutes (degree of dryness 1)	DIN EN ISO 9117-5
<b>Dry to the touch</b>	after 4 hours (degree of dryness 4)	DIN EN ISO 9117-5
<b>Full drying</b>	after 8 day/s (pendulum damping)	DIN EN ISO 1522
<b>Cleaning of equipment</b>	immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916, dried-on equipment with org. solvents, e.g. EFD thinner 400424. Do not mix curing agent with water! The cleaning must be carried out with organic solvents.	

### Further processing of coated pieces

<b>Repainting</b>	possible with same quality, dry at the earliest after matting.
-------------------	--

### Comments

<b>EFD info</b>	Further technical information can be found in the EFD Info. No. 111 + 510.
<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.