



WU1458H_HU0448 EFDEDUR-Hydro-Coating

Product description

Product technology	water-thinnable 2C coating
Application area	e.g. in the mechanical engineering and plant construction sector
Drying	quickly
Mechanical resistance	good
Substrate	Steel, Primer

General product properties

Binder-Base	Acrylic Resin
Colour	All common colour shades
Gloss value	satin glossy 55-70 GU, angle 60° DIN EN ISO 2813
Viscosity	Flow time 28-38 sec. 4 mm flow cup DIN 53211
pH-Value	8,0-8,5 DIN 19260
Solid mass	49-53 % after addition of hardener theoretical
Solid content in volume	38-41 % after addition of hardener theoretical
Reference product	The values given refer to the product with the shade WU1458HK2916.
Resistance to storage	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>



WU1458H_HU0448 EFDEDUR-Hydro-Coating

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Structure recommendation	Substrate	KTL primed
Note before use	Top coat	
Hardener	WU1458HK2916	
Mixin ratio	Mixing ratio 6:1/ HU0448	
Thinning	Dry film thickness μm	
Dry film thickness	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.	
Object temperature	HU0448 see technical data sheet	
Processing conditions	Parts by weight 6:1	
Processing time	Volume parts 5:1	
Airmix spraying	demineralised water	
High pressure spraying	must not exceed 80 μm – risk of reaction bubbles.	
Rolling/painting	10-30 °C, minimum +3 °C above dew point temperature	
Material usage	Room temperature 18-22 °C	
Oven drying	Relative humidity 40-60 %	
Air drying	max. 4 hrs. / 20 °C	
	End of the processing time cannot be detected from gelling. The processing time can decrease at higher temperatures and/or under pressure.	
	30-40 sec. / 4 mm viscosity cup	DIN 53211
	Nozzle 0,23 mm angle 30°	
	Material pressure 80 bar	
	Atomiser pressure 3 bar	
	30-40 sec. / 4 mm Flow cup	DIN 53211
	Nozzle 1,5 mm	
	Injection pressure 3 bar	
	as delivered viscosity	
	without application loss 110-130 g/m ²	theoretical
	layer thickness 40 μm after addition of hardener	
	up to 80 °C possible	
	18-22 °C, 40-60 % relative humidity	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510

www.freilacke.de | info@freilacke.de



WU1458H_HU0448 EFDEDUR-Hydro-Coating

Dust drying	after 30 minutes (degree of dryness 1)	DIN EN ISO 9117-5
Dry to the touch	after 4 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 8 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916, dried-on equipment with org. solvents, e.g. EFD thinner 400424. Do not mix curing agent with water! The cleaning must be carried out with organic solvents.	

Further processing of coated pieces

Repainting	possible with same quality, dry at the earliest after matting.
-------------------	--

Comments

EFD info	Further technical information can be found in the EFD Info. No. 111 + 510.
Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.