



**FREIOTHERM-KTL-Special**  
WK4906HRU905

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>■ Cathodic electrocoat paint depositable 2K</li> <li>■ Application, e.g. in the job coater sector</li> <li>■ Pigment paste, fully neutralised</li> <li>■ Primer</li> <li>■ Good corrosion protection</li> </ul>												
<b>Technical / Physical Data</b>	<table border="1"> <tr> <td>■ Binder-Base</td> <td>Expoxy Resin, modified</td> </tr> <tr> <td>■ Colour</td> <td>black Based on the specified colour template (i.e. RAL)</td> </tr> <tr> <td>■ Solid Mass <small>DIN EN ISO 3251</small></td> <td>44-48 %</td> </tr> <tr> <td>■ Density <small>calculated</small></td> <td>1,21 g/cm<sup>3</sup></td> </tr> <tr> <td>■ MEQ/s-Value</td> <td>42-47 mmol/100g</td> </tr> <tr> <td>■ Test layer thickness</td> <td>15-20 µm</td> </tr> </table>	■ Binder-Base	Expoxy Resin, modified	■ Colour	black Based on the specified colour template (i.e. RAL)	■ Solid Mass <small>DIN EN ISO 3251</small>	44-48 %	■ Density <small>calculated</small>	1,21 g/cm <sup>3</sup>	■ MEQ/s-Value	42-47 mmol/100g	■ Test layer thickness	15-20 µm
■ Binder-Base	Expoxy Resin, modified												
■ Colour	black Based on the specified colour template (i.e. RAL)												
■ Solid Mass <small>DIN EN ISO 3251</small>	44-48 %												
■ Density <small>calculated</small>	1,21 g/cm <sup>3</sup>												
■ MEQ/s-Value	42-47 mmol/100g												
■ Test layer thickness	15-20 µm												
<b>Mechanical Test</b>	<table border="1"> <tr> <td>■ on zinc phosphate</td> <td></td> </tr> <tr> <td>■ Cross-cut-test <small>DIN EN ISO 2409</small></td> <td>Gt 0</td> </tr> <tr> <td>■ Erichsen index <small>DIN EN ISO 1520</small></td> <td>4 mm</td> </tr> <tr> <td>■ Mandrel bending test cylindrical <small>DIN EN ISO 1519</small></td> <td>8 mm</td> </tr> </table>	■ on zinc phosphate		■ Cross-cut-test <small>DIN EN ISO 2409</small>	Gt 0	■ Erichsen index <small>DIN EN ISO 1520</small>	4 mm	■ Mandrel bending test cylindrical <small>DIN EN ISO 1519</small>	8 mm				
■ on zinc phosphate													
■ Cross-cut-test <small>DIN EN ISO 2409</small>	Gt 0												
■ Erichsen index <small>DIN EN ISO 1520</small>	4 mm												
■ Mandrel bending test cylindrical <small>DIN EN ISO 1519</small>	8 mm												
<b>Resistance Test</b>	<table border="1"> <tr> <td>■ on zinc phosphate</td> <td></td> </tr> <tr> <td>■ Condensate constant climate <small>DIN EN ISO 6270-2 (CH)</small></td> <td>504 hours water ingress Wb &lt;0,5 mm DIN EN ISO 4628-8</td> </tr> <tr> <td>■ Salt spray test (NSS) <small>DIN EN ISO 9227</small></td> <td>1008 hours water ingress Wb &lt;2 mm DIN EN ISO 4628-8</td> </tr> <tr> <td>■ Climate Change Test <small>DIN EN ISO 11997-1-B</small></td> <td>10 cycles water ingress Wb &lt;1 mm DIN EN ISO 4628-8</td> </tr> </table>	■ on zinc phosphate		■ Condensate constant climate <small>DIN EN ISO 6270-2 (CH)</small>	504 hours water ingress Wb <0,5 mm DIN EN ISO 4628-8	■ Salt spray test (NSS) <small>DIN EN ISO 9227</small>	1008 hours water ingress Wb <2 mm DIN EN ISO 4628-8	■ Climate Change Test <small>DIN EN ISO 11997-1-B</small>	10 cycles water ingress Wb <1 mm DIN EN ISO 4628-8				
■ on zinc phosphate													
■ Condensate constant climate <small>DIN EN ISO 6270-2 (CH)</small>	504 hours water ingress Wb <0,5 mm DIN EN ISO 4628-8												
■ Salt spray test (NSS) <small>DIN EN ISO 9227</small>	1008 hours water ingress Wb <2 mm DIN EN ISO 4628-8												
■ Climate Change Test <small>DIN EN ISO 11997-1-B</small>	10 cycles water ingress Wb <1 mm DIN EN ISO 4628-8												
<b>Processing and application</b> Dependent on plant and buildings	<table border="1"> <tr> <td>■ <b>Pretreatment</b></td> <td>The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. For more demanding requirements on corrosion inhibiting properties, we recommend suitable conversion processes (e.g. phosphatizing).</td> </tr> <tr> <td>■ Mixing ratio</td> <td>4:1 WK4038 : WK4906</td> </tr> <tr> <td>■ Gloss value <small>DIN EN ISO 2813</small></td> <td>30-50 geometry 60°</td> </tr> <tr> <td>■ pH-Value</td> <td>5-6</td> </tr> <tr> <td>■ Cunductance</td> <td>800-1200 µS/cm</td> </tr> <tr> <td>■ Solid Mass <small>DIN EN ISO 3251</small></td> <td>12-14 %</td> </tr> </table>	■ <b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. For more demanding requirements on corrosion inhibiting properties, we recommend suitable conversion processes (e.g. phosphatizing).	■ Mixing ratio	4:1 WK4038 : WK4906	■ Gloss value <small>DIN EN ISO 2813</small>	30-50 geometry 60°	■ pH-Value	5-6	■ Cunductance	800-1200 µS/cm	■ Solid Mass <small>DIN EN ISO 3251</small>	12-14 %
■ <b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. For more demanding requirements on corrosion inhibiting properties, we recommend suitable conversion processes (e.g. phosphatizing).												
■ Mixing ratio	4:1 WK4038 : WK4906												
■ Gloss value <small>DIN EN ISO 2813</small>	30-50 geometry 60°												
■ pH-Value	5-6												
■ Cunductance	800-1200 µS/cm												
■ Solid Mass <small>DIN EN ISO 3251</small>	12-14 %												

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



**FREIOTHERM-KTL-Special**  
**WK4906HRU905**

	■ MEQ/b-Value	5,5-7,0 mmol/100 g
	■ Organic Solvent Content	1,5-3,0 %
	■ Bath Temperature	32-34 °C
	■ Coating Time	120-240 seconds
	■ Deposition Voltage	150-300 voltage
	<b>■ Health &amp; Safety at Work guidelines</b> The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.	

**Curing**

■ **Object temperature**  
 Recommended baking temperature 20 Min./150 °C

green cross-hatching = baking conditions with good final properties

**Resistance to storage**

■ One Turn-Over per year

Approx. 9 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.

The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

**Specific comments**

■ **Test conditions**  
 All information is based on a standard climate 23/50 DIN EN 23270.  
 All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  
 The information provided here contains reference values and does not constitute a specification.