

EFDEDUR

Pearl-Structure laquer GS1007M

- Two component structure paint with solvent
- For indoor and outdoor usage
- Silicone-free
Self-creating pearl structure in one layer

Technical / physical data	Resin/ binder	polyacrylic to be hardened with isocyanate
	Colour	acc. to RAL 840 HR other colour shades on request
	Gloss value visual	mat
	Original viscosity without hardener	200 to 2000 mPa.s / Spindel 4
	Mixing ratio by weight	5 : 1
	Hardener base	EFDEDUR-Hardener HU0001 polyisocyanate
	Potlife after hardener addition	approx. 6 h / 20 °C
	Thinner	EFD-Thinner 400320 or EFD-Thinner 400500
	Density after hardener addition calculated	1,4 g / ml + / - 0,1
	Solid content after hardener addition calculated	60 % + / - 2
	Solid content in volume after hardener addition calculated	450 ml / kg + / - 10
	Material usage calculated, after hardener addition in original viscosity, without application loss	100 to 120 g / m ² dry film thickness 40 to 60 µm
	Spreading rate calculated after hardener addition in original viscosity, without application loss	8,5 to 9,5 m ² / kg dry film thickness 40 to 60 µm see „Special remarks“

EFDEDUR

Pearl-Structure laquer
GS1007M

FreiLacke



Storability

Approx. 24 month in original packings at an ambient temperature of 5 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective.

Processing and application

Application

Components are to be mixed homogeneously (e.g. with high-speed mixer).

Pneumatic spraying: after hardener addition

nozzle: 1,2 to 1,8 mm spraying pressure: 3 to 5 bar

Substrates

steel, non ferrous metals, different plastics

Pretreatment

The substrate must be free of materials which prevent adhesion, e.g. oil, grease, dust and surfactant. According to the requirements we recommend to apply the suited chemical (e.g. phosphatizing, chromating) or / and mechanical (e.g. shot blasting) pretreatment.

Proposal for a coating system

substrate: steel

primer: FREIOPOX-Primer ER1912

top coat: Pearl-Structure laquer GS1007M

Application temperature

above 10 °C

Drying

air drying at 20°C

dust dry: after 30 min. (degree of drying 1 / DIN EN ISO 9117-5)

dry to touch: after 1,5 h (degree of drying 4 / DIN EN ISO 9117-5)

complete dry: after 5 days (swinging beam hardness /DIN EN ISO 1522)

oven drying: to 100°C possible (object temperature)

Cleaning of working equipment

EFD-Thinner 400500

Advise for safety protection and protection of health

The usual precautionary measures for ventilation as well as for personal protection are to be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning health protection and environment protection can be read in the corresponding safety data sheet.

Special remarks

Test condition

The statements concerning efficiency, drying and caution labelling depend on colour shade. The values mentioned in this data sheet are based on GS1007MRA712, mat and hardening with EFDEDUR-Hardener HU0001.

All information is based on a standard climate 20/65 DIN 50014.

For the calculation of the practical consumption loss additions have to be considered. Indications to this are the practical experience and advices given in DIN 53220.

All information are based on our product knowledge and experience. To the application we have no direct influence. For further information please don't hesitate to contact us.

The information mentioned herein are reference values and are not given as specification.