



GS1041L_HU0001 EFDEDUR-Structure Coating

Product description

Product technology	solvent-based 2-component coating		
Surface	Different structures are possible depending on application and viscosity.		
Application	For interior and exterior applications		
Property	Silicone-free		
Drying	quickly		
Full drying	fast complete drying		
Substrate	Steel		

General product properties

Binder-Base	Acrylic Resin		
Colour	in accordance with RAL 840 HR other colours on request		
Gloss value	satin mat	20-30 GU, Angle 60° The degree of gloss is strongly dependent on the structure. The given value refers to a smooth, weakly structured surface.	DIN EN ISO 2813
Viscosity	3500-4500 mPa*s, spindle 5, 60 revolutions/min.		DIN EN ISO 2555
Density	1,25-1,35 g/ml after addition of hardener		theoretical
Solid mass	64,0-66,0 % after addition of hardener		theoretical
Solid content in volume	48,5-49,5 % after addition of hardener		theoretical
Reference product	The specified values refer to the product GS1041LRA716.		
Resistance to storage	approx. 24 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.		
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.		

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.		
Structure recommendation	Substrate	Steel	



GS1041L_HU0001 EFDEDUR-Structure Coating

Primer	ER1912M Mixing ratio 5:1 HE0052 Dry film thickness 70-90 µm
Top coat	GS1041L Mixing ratio 6:1 HU0001 Dry film thickness 40-60 µm
Note before use	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).
Hardener	HU0001
Mixin ratio	Parts by weight 6:1 HU0001
Thinning	EFD dilution 400320 EFD dilution 400500
Processing conditions	from 10 °C to 25 °C
Processing time	max. 6 hrs. / 20 °C The processing time can decrease at higher temperatures and/or under pressure.
High pressure spraying	Following the addition of the curing agent, set the processing viscosity in accordance with the respective application process. Depending on the desired texture, the application takes place in one (self-forming texture) or in two operations (sprinkle effect): 1.) Self-forming texture (one operation) e.g. Sata jet® Nozzle 1,5-2,0 mm Spray pressure 3-5 bar Cross coats 1-2 2.) Sprinkle effect (two operations A + B) e.g. Sata jet® Nozzle 1,5-2,0 mm Cross coats 1-2 A) Spray pressure 3-5 bar, smooth pre-spraying following the drying of the coating surface (approx. 30 min. / 20°C) B) Sprinkle the desired texture using reduced spray pressure Spray pressure 0,5-2,0 bar By changing the spray pressure, nozzle diameter, coating viscosity, spray guns and system setting, different surface textures can be achieved. Any wearing of the nozzles and system must be taken into account. Additional application options must be tested.
Rolling/painting	rolling/painting e.g. with microfibre roll
Electrostatic	possible, system-specific
Material usage	without application loss 125-135 g/m ² theoretical layer thickness 50 µm after addition of hardener
Oven drying	up to 100 °C possible (object temperature)
Air drying	20 °C, 50 % relative humidity
Dust drying	after 30 minutes (degree of dryness 1) DIN EN ISO 9117-5

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business, delivery and payment.



GS1041L_HU0001 EFDEDUR-Structure Coating

Dry to the touch	after 5 hours (degree of dryness 4)	DIN EN ISO 9117-5
Full drying	after 8 day/s (pendulum damping)	DIN EN ISO 1522
Cleaning of equipment	EFD dilution 400500	

Comments

Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.