

DURELASTIC

Pigment Paste BD7502XM2093

- Binder based on unsaturated polyester resin, with styrene
- High concentration
- High colouring power

Technical / Physical data	Colour	black other colour shades on request
	Original viscosity	1400 to 3000 m.Pa.s/ 23°C spindle 6, stage 50, Brookfield RVT
	Density calculated	1,2 g / ml +/- 0,1
Storability	Approx. 4 month in original packings at an ambient temperature of 15 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective	
Processing and application	Application	in original viscosity
	Addition of	2 to 5 % for colouring of resins 10 to 15 % for colouring of top coat resins
	Cleaning of working equipment	EFD-Cleaning agent 400906
Special remarks	Advise for safety protection and protection of health The usual precautionary measures for ventilation as well as for personal protection are to be observed when handling painting materials. Detailed information about dangerous goods, sayfety data and recommendations concerning health protection and environment protection can be read in the corresponding safety data sheet.	
	Test conditions All information is based on a standard climate 20/65 DIN 50014.	
	All information are based on our product knowledge and experience. To the application we have no direct influence. For further information please don't hesitate to contact us. The information mentioned herein are reference values and are not given as specification.	