



## PD7004A FREOPOX-Powder Coating

### Product description

<b>Product technology</b>	Powder coating primer for powder-in-powder application
<b>Application area</b>	Application, e.g. in the vehicle construction sector
<b>Over-coating capability</b>	very good
<b>Corrosion protection</b>	very good

### General product properties

<b>Binder-Base</b>	Epoxy Resin
<b>Colour</b>	All common colour shades
<b>Gloss visually</b>	glossy
<b>Density</b>	1,2-1,7 g/cm <sup>3</sup> depending on the shade <span style="float: right;">theoretical</span>
<b>Resistance to storage</b>	<p>approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>

### Application and processing


<b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.
<b>Recommended coating thickness</b>	60-80 µm
<b>Material usage</b>	approx. 0,12 kg/m <sup>2</sup> , layer thickness 80 µm <span style="float: right;">theoretical</span>
<b>Processing</b>	Tribo



## PD7004A FREOPOX-Powder Coating

### Curing

Recommended object temperature 10 min/160 °C.  
Baking window tested in colour shade 9002.



Objekt Temperatur in °C Object Temperature in °C	160	180	200
Haltezeit Minimum in Minuten Holding time minimum in minutes	10	8	5
Haltezeit Maximum in Minuten Holding time maximum in minutes	60	30	15

### Note on curing

Coloured area = stoving conditions with good end properties

The displayed baking conditions are based on results from laboratory tests and therefore merely serve as a guideline when configuring the processing company's coating systems. The processing company is responsible for ensuring that the coating is fully cured. The complete curing of the coating must be checked by means of additional analytical and resistance tests using representative original parts under production conditions. Please do not hesitate to contact us if you require consultation.

### Compatibility

Compatibility with other powder coatings must be checked.

## Further processing of coated pieces

### Touch-up coating

on request. For details see EVS Info No. 4..

## Mechanical tests

### Sample description

On steel plate  
60-80 µm layer thickness  
10 minutes 160°C object temperature  
product PD7004ARG902

### Cross-cut-test

Gt 0

DIN EN ISO 2409

### Cupping test

>3 mm

DIN EN ISO 1520

### Impact-test

>70 kg cm (front)

DIN EN ISO 6272-1



## PD7004A FREOPOX-Powder Coating

### Comments

#### Work-and Healthprotection

The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.

#### EFD info

Further technical information can be found in the EFD Info. No. 511

#### Test conditions

All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.