



WA4938HRU905 FREIOTHERM-ATL-Catalysator

Product description

Product technology	anodic electrocoat paint depositable 1K
Application area	e.g. in the mechanical engineering and plant construction sector
Type of paste	Special Paste
Corrosion protection	very good

General product properties

Binder-Base	Acrylic-Epoxy Resin	
Viscosity	2000-6000 mPa*s	
MEQ-Base-Value	28-35 mg/g	DIN EN ISO 15880
Density	1,0-1,2 g/cm³	theoretical
Solid mass	53-57 %	theoretical
Resistance to storage	approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Gloss value	40-60 GU, Angle 60°	DIN EN ISO 2813
Recommended coating thickness	12-25 µm	
pH-Value	8,3-8,6	DIN 19260
Cunductance	1700-2700 µS/cm	
Solid mass	17-19 %	DIN EN ISO 3251
MEQ-Base-Value	55-65 mg/g	DIN EN ISO 15880
Organic Solvent Content	0,6-2,0 %	
Bath Temperature	24-27 °C	
Coating Time	60-180 sec.	
Deposition Voltage	100-220 Volts	



WA4938HRU905
FREIOTHERM-ATL-Catalysator

Turn-over

1 Turnover per year
To ensure bath stability and thus the coating quality, the specified turnover (solids exchange of the tank) must be observed.

Mechanical tests

Test substrate	on steel, purified alkaline	
Cross-cut-test	Gt 0	DIN EN ISO 2409

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	<p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</p> <p>The information provided here contains reference values and does not constitute a specification.</p>