



## BD7869XRU735

### DURELASTIC-Laminating Resin

#### Product description

<b>Product technology</b>	Cobalt pre-accelerated
<b>Application</b>	Suitable for cold hardening and hot pressing

#### General product properties

<b>Binder-Base</b>	unsaturated polyester resin, styrene containing	
<b>Colour</b>	Light grey	
<b>Viscosity</b>	Flow time 45 sec. 6 mm flow cup	DIN 53211
<b>Density</b>	1,1 +/- 0,1 g/ml	theoretical
<b>Solid mass</b>	60 - 64 %	theoretical
<b>Resistance to storage</b>	<p>approx. 4 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p> <p>As the time in storage increases, the gelling and curing times can change. The original gelling time can be adjusted by adding accelerators ( e.g. BD7550 ).</p>	

#### Application and processing

<b>Tool/mould</b>	<p>Separating film</p> <p>GRP types (of glass fibre-reinforced plastic)</p> <p>Metal molds</p>
<b>Pretreatment</b>	Treat moulds with suitable separating agents.
<b>Note before use</b>	Prior to use, stir well or mix components homogeneously (e.g. with fast mixer).
<b>Hardener</b>	2 % Curox A 140
<b>Thinning</b>	EFD dilution 400900
<b>Processing conditions</b>	During processing, a room, material and mould temperature of [Variable] °C must be guaranteed in order to prevent hardening problems and cracking.
<b>Processing time</b>	<p>max. 100 min. / 20 °C</p> <p>With the addition of 2 % Curox A 140</p>
<b>Application</b>	as delivered viscosity.
<b>Cleaning of equipment</b>	with EFD cleaning agent 400906 within the processing time.



## BD7869XRU735 DURELASTIC-Laminating Resin

### Mechanical tests

<b>mechanical properties</b>	Barcol hardness 934-1	50	DIN EN 59
	HDT	105 °C	DIN EN ISO 75-2
	Bending strength	120 MPa	DIN EN ISO 178
	E-module	4200 MPa	DIN EN ISO 178
	This information refers to the cured, unreinforced pure resin.		

### Comments

<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.