

EFDEDUR

System-Paint UR9140

- 2-component-polyurethane-finish paint with solvent
- On powder coating co-ordinated system
- In- and outdoor usage
- For industrial goods, e.g. mechanical engineering
- Good working properties

Technical / Physical Data	Resin/ binder	polyacrylic resin to be hardened with isocyanate	
	Colour	between powder coating and RAL-Colour, RAL 840 HR	
	Gloss value	after powder sample	
	Original viscosity DIN 53211* without hardener	90 to 120 Sek. / 4 mm cup	
	Mixing ratio by weight	UR9140G =	4 : 1
		UR9140H =	5 : 1
		UR9140M	10 : 1
	Hardener base	EFDEDUR-Hardener polyisocyanate see „Special remarks“	HU0001
	Potlife after hardener addition	max. 6 h / 20°C	
	Thinner	EFD-Thinner	400018, 400320 or 400500
	Density after hardener addition calculated	1,25 g / ml + / - 0,15	
	Solid content after hardener addition calculated	65 % + / - 2	
	Solid content in volume after hardener addition calculated	400 ml / kg + / - 20	
	Consumption calculated after hardener addition in original viscosity, without application loss	120 bis 130 g / m ² dry film thickness 50 µm see „Special remarks“	

Storability Approx. 24 month in original packings at an ambient temperature of 5 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective

Processing and application

Application

Components are to be mixed homogeneously (e.g. with high-speed mixer).

spraying-highpressure: after hardener addition and viscosity adjustment to 18 to 22 sec.
nozzle: 1,8 mm spraying pressure: 3 to 4 bar
by roller/ brush: in original viscosity after hardener addition

For roller and brush application add. 0,5 to 1,0 % by weight EFD-deaeration agent 300807 in case of bubble creation.

Substrates

steel, non ferrous metals, wood, plastic: e.g. PA, ABS, GFK

Pretreatment

The substrate must be free of materials which prevent adhesion, e.g. oil, grease, dust and surfactant. According to the requirements we recommend to apply the suited chemical (e.g. phosphatizing, chromating) or / and mechanical (e.g. shot blasting) pretreatment.

Proposal for a coating system 1

substrate: steel
primer: FREOPOX-Primer ER1912
top coat: EFDEDUR-System-Paint UR9140

Proposal for a coating system 2 – as one coat paint (no outdoor usage)

substrate: steel
top coat: EFDEDUR-System-Paint UR9140

Application temperature

above 10 °C

Drying

air drying at 20°C

dust dry:	after 60 min.	(degree of drying 1/ DIN EN ISO 9117-5)
dry to touch:	after 5 h	(degree of drying 4/ DIN EN ISO 9117-5)
complete dry:	after 9 days	(swinging beam hardness/ DIN EN ISO 1522)
oven drying:	to 100°C possible	(object temperature)

Cleaning of working equipment

EFD-Thinner 400500

Advise for safety protection and protection of health

The usual precautionary measures for ventilation as well as for personal protection are to be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning health protection and environment protection can be read in the corresponding safety data sheet.

Special remarks

Information about Hardener and Thinner

The hardener and the thinner mentioned on page 1 are stated as standard components for this paint system. The standard hardener is also written in the order documents as well as on the label.

Furthermore there are additional hardeners and thinners, which can be used as alternative in case the standard components doesn't meet the requirements. These products are tailor-made e.g. faster or slower hardening.

Hardener are taking influence on the gloss (see page 1).

Test condition

*Indication of the delivery viscosity according to DIN 53211:

DIN 53211 was withdrawn in October 1996. On request the value is available according to DIN EN ISO 2431.

The statements concerning efficiency and drying depend on colour shade.
The values mentioned in this data sheet are based on UR9140HH2940, reseda green,
in satin mat adjustment.

All information is based on a standard climate 20/65 DIN 50014.

For the calculation of the practical consumption loss additions have to be considered.
Indications to this are the practical experience and advices given in DIN 53220.

All information are based on our product knowledge and experience. To the application we
have no direct influence. For further information please don't hesitate to contact us.

The information mentioned herein are reference values and are not given as specification.