

DURELASTIC

Accelerator BD7550

- Accelerator on base of Cobaltoctoat in styrene
- Proportion of Cobaltoctoat: 1,8 %

Technical / Physical data	Colour	violet
	Original viscosity DIN 53211*	12 to 15 sec. / 4 mm cup 42 to 48 sec. / 2 mm cup
	Addition quantity (by weight)	0,2 bis 2,0 % , as required
	Thinner	DURELASTIC-resin thinner 400900
	Density calculated	0,95 g / ml + / - 0,05
	Solid content calculated	approx. 11 %
Storability	Approx. 6 month in original packings at an ambient temperature of 15 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective.	
Processing and application	Processing	The accelerator addition depends on the respective use.
	Attention:	Accelerators BD7550 and hardener separately mix and store!
	Cleaning of working equipment	During pot life: EFD-cleaning agent 400312
Special remarks	Advise for safety protection and protection of health	The usual precautionary measures for ventilation as well as for personal protection are to be observed when handling painting materials. Detailed information about dangerous goods, sayfety data and recommendations concerning health protection and environment protection can be read in the corresponding safety data sheet.
	Test conditions	*Indication of the delivery viscosity according to DIN 53211: DIN 53211 was withdrawn in October 1996. On request the value is available according to DIN EN ISO 2431.
		All information is based on a standard climate 20/65 DIN 50014. All information are based on our product knowledge and experience. To the application we have no direct influence. For further information please don't hesitate to contact us. The information mentioned herein are reference values and are not given as specification.