PB1312A
FREOPOX-Powder Coating

Product description

Product technology	Powder coating for interior use
Application area	e.g. in the functional furniture and storage technology sector
Surface	micro structure
Gloss value	satin mat
Degassing	very good
Surface hardness	good
Mechanical resistance	good

General product properties

Binder-Base	epoxy polyester resin	
Colour	All common colour shades	
Gloss visually	satin mat	
Density	1,2-1,7 g/cm³ depending on the shade	theoretical
Resistance to storage	approx. 36 month in original packagings at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

Application and processing

Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, mill scale, wax and release agent residues. We recommend the use of suitable mechanical pre-treatment processes (e.g. blasting, grinding) or chemical pre-treatment processes (e.g. phosphating) according to the requirements.	
Recommended coating thickness	Uniform surface structure across a range of 70 to 110 µm	
Material usage	approx. 0,12 kg/m², layer thickness 80 µm	theoretical
Processing	Corona, Tribo	


Our technical data sheets are to provide you with advice based on our latest state of knowledge.
This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.
The sale of our products is in accordance with our terms of business, delivery and payment.

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de

PB1312A
FREOPOX-Powder Coating

Curing	Recommended object temperature 10 min/180 °C. Baking window tested in colour shade RA7024.



Objekt Temperatur in °C Object Temperature in °C	160	180	200
Haltezeit Minimum in Minuten Holding time minimum in minutes	15	10	6
Haltezeit Maximum in Minuten Holding time maximum in minutes	60	45	30

Note on curing	Coloured area = stoving conditions with good end properties The displayed baking conditions are based on results from laboratory tests and therefore merely serve as a guideline when configuring the processing company's coating systems. The processing company is responsible for ensuring that the coating is fully cured. The complete curing of the coating must be checked by means of additional analytical and resistance tests using representative original parts under production conditions. Please do not hesitate to contact us if you require consultation.
Compatibility	Compatibility with other powder coatings must be checked.

Further processing of coated pieces

Touch-up coating	on request. For details see EFD Info No. 4..

Mechanical tests

Sample description	On steel plate 70-90 µm layer thickness 10 minutes 180°C object temperature product PB1312ARA724	
Cross-cut-test	Gt 0	DIN EN ISO 2409
Cupping test	>3 mm	DIN EN ISO 1520
Impact-test	>60 kg cm (front)	DIN EN ISO 6272-1

Our technical data sheets are to provide you with advice based on our latest state of knowledge.
This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.
The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de

PB1312A
FREOPOX-Powder Coating

Climatic tests

Sample description	On iron-phosphated steel plate product PB1312ARA724		
Condensate constant climate	Load duration Detachment Cut	500 h <1 mm	DIN EN ISO 6270-2 (CH) DIN EN ISO 4628-8
Neutral salt spray test	Load duration Detachment Cut	240 h <1 mm	DIN EN ISO 9227 (NSS) DIN EN ISO 4628-8

Chemical resistance

Influencing factors	The chemical resistance depends on the concentration, temperature, exposure time and test method. This has to be checked depending on the application.

Comments

Work-and Healthprotection	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.

Our technical data sheets are to provide you with advice based on our latest state of knowledge.
This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.
The sale of our products is in accordance with our terms of business, delivery and payment.

FreiLacke | Emil Frei GmbH & Co. KG

Am Bahnhof 6
78199 Bräunlingen-Döggingen | Deutschland
+49 77071510
www.freilacke.de | info@freilacke.de