



## BD7521X

## DURELASTIC-Pigment paste

### Product description

<b>Property</b>	colour intensive
<b>Pigment content</b>	highly concentrated

### General product properties

<b>Binder-Base</b>	Unsaturated, styrene-free polyester resin	
<b>Colour</b>	in accordance with RAL 840 HR other colours on request	
<b>Viscosity</b>	Flow time 30 - 40 sec., 4 mm flow cup	DIN 53211
<b>Density</b>	2,0 +/- 0,1 g/cm <sup>3</sup> depending on the shade	theoretical
<b>Solid mass</b>	ca. 89 %	theoretical
<b>Resistance to storage</b>	approx. 11 month in original packagings at an ambient temperature of 5 to 25 °C. Open packages are to be used within a short time.	
	The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	

### Application and processing

<b>Note before use</b>	Carry out pretesting, as pigments may delay or extend pot lives depending on the colour shade.
<b>Application</b>	as delivered viscosity 2 - 5 % for colouring resins 10 - 15 % for colouring cover layer resins
<b>Cleaning of equipment</b>	EFD cleaning agent 400906

### Comments

<b>Work-and Healthprotection</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health and Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.