Technical Data Sheet





BD7500XDURELASTIC-Pigment paste

Product description

Property colour intensive

Resistance to light and

weather

Pigment content

good

highly concentrated

General product properties

Binder-Base Unsaturated, styrene-free polyester resin

Colour in accordance with RAL 840 HR

other colours on request

Viscosity 3.000 - 35.000 mPa*s, spindle 5, 20 revolutions/min. DIN EN ISO 2555

Density 1,2 - 2,2 g/cm³ depending on the shade theoretical **Solid mass** 10 - 58 % theoretical

Resistance to storage approx. 11 month in original packagings at an ambient temperature of 5 to 25 °C. Open

packages are to be used within a short time.

The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

Application and processing

Note before use Carry out pretesting, as pigments may delay or extend pot lives depending on the colour

shade.

Application as delivered viscosity

2 - 5 % for colouring resins

10 - 15 % for colouring cover layer resins

Cleaning of equipment EFD cleaning agent 400906

Comments

Work-and
The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and

recommendations concerning Health and Safety at Work and environmental protection

can be found in the corresponding safety data sheet.

Test conditions All information is based on a standard climate 23/50 DIN EN 23270. All information is

based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications.

The sale of our products is in accordance with our terms of business, delivery and payment.

DIN EN ISO 9001 | IATF 16949 | EMAS

Am Bahnhof 6 78199 Bräunlingen-Döggingen | Deutschland

FreiLacke | Emil Frei GmbH & Co. KG

www.freilacke.de | info@freilacke.de

+49 77071510

Page 1/1 | Version 0 Revision date: Jan 29, 2025 Print date: Jan 29, 2025